Daily Test Report Checklist – IGU - Spacer Bar System

Company Name		CSi Licence ID. No.	Location	
Northern Glass Solutions Pty Ltd		7709	84 O'Sullivan Circuit, East Arm, NT 0822.	
Applicable Certified Product Standard:	☐ AS 4666:2012 Insulating glass units + Amd No1:2018		☐ Other :	
Report Completed By:	**1.**	**2.**	**3.**	**4.**

Check List Item No.	Standard requirement to be verified.
1.	☒ **AS 4666:2012 Section 5.8.2 & 6.0** Number of IGU Units to be sampled from a production lot and tested daily (From Table 6.1, AS 4666).

NUMBER OF UNITS TO CHECK PER SHIFT (Table 6.1)	
2 - 5	1
16 - 25	2
26 - 90	3
91 - 150	4
151 - 500	6
501 - 1200	10
1201 - 9999	16
Activity Completed ☐ **Yes** ☐ No (Records maintained for 5.8.2 if non-conforming product is found, another product shall be inspected in its place)	
Notes:	

Check List Item No.	Standard requirement to be verified.
2.	☐ **AS 4666:2012 Section 5.2** Record Atmospheric Conditions at start of production shift and every four (4) hours until the end of production shift.

Date:		**Time Shift Start:**		**Time Shift Finish:**		**Total Units Produced:**	
Time:		**Temp 0°c:**		**Relative Humidity:**		**Barometric Pressure:**	
Time:		**Temp 0°c:**		**Relative Humidity:**		**Barometric Pressure:**	
Time:		**Temp 0°c:**		**Relative Humidity:**		**Barometric Pressure:**	
Time:		**Temp 0°c:**		**Relative Humidity:**		**Barometric Pressure:**	
Time:		**Temp 0°c:**		**Relative Humidity:**		**Barometric Pressure:**	
Time:		**Temp 0°c:**		**Relative Humidity:**		**Barometric Pressure:**	
Activity Completed ☐ **Yes** ☐ No (Records maintained for 5.2)							
Notes:							

COMPONENT CHECKED:	Glazing Materials

Check List Item No.	Standard requirement to be verified.
3. 3.1	☐ **AS 4666:2012 Section 5.3.1, 5.3.2 and 5.3.3** GLASS: Compliance with order – Traceability – Types of Substrates **Compliance with order** ☐ **Pass:** / **Compliance with order** ☐ **Fail:** **Notes:** 1. (5.3.1) The company maintains a permanent record of glazing materials, date of receipt and compliance with order specification for the completed insulating glass units. Thickness limits for glazing materials are given in Table 5.1, measured in accordance with. Appendix A, AS 4666. 2. (5.3.2) The company maintains a system that ensures glazing material types included in the fabrication of an insulating glass unit are traceable, records shall be maintained. To be conducted every customer order. **Signature.** *Activity Completed* ☐ **Yes** ☐ No (Records maintained for 5.3.1 & 5.3.2)
3.2	☐ **AS 4666:2012 Section 5.3.4** GLASS: Edge Characteristics. A visual inspection shall be conducted in accordance with Section 5.3.4 and Table 5.2 **Edge Characteristics Check** ☐ **Pass:** / **Edge Characteristics Check** ☐ **Fail:** **Notes:** To be conducted every customer order or every half hour whichever is the lesser. **Signature.** *Activity Completed* ☐ **Yes** ☐ No
3.3	☐ **AS 4666:2012 Section 5.3.5** GLASS: Dimensional Properties: When measured in accordance with Appendix A, AS 4666 – THICKNESS tolerance monolithic glass see, Table 5.1, FLATNESS (Bow) see Table 5.3, HEIGHT/WIDTH, Refer to Section 5.3.5.2, Residential Units, Section 5.3.5.3, Commercial Units. **Dimensional Properties Check** ☐ **Pass:** / **Dimensional Properties Check** ☐ **Fail:** **Notes:** A visual inspection to be conducted every customer order or every half hour whichever is the lesser. **Signature.** *Activity Completed* ☐ **Yes** ☐ No
3.4	☐ **AS 4666:2012 Section 5.3.6** GLASS: Cleanliness: A visual inspection shall be conducted for Dryness, Stains/Films, and Fingerprints. **Glazing Cleanliness Check** ☐ **Pass:** / **Glazing Cleanliness Check** ☐ **Fail:** **Notes:** 100% inspection all glazing materials. Particular attention to internal surfaces. **Signature.** *Activity Completed* ☐ **Yes** ☐ No (Records required if Stains/Films cannot be removed, size & location to be recorded)

3.5	☐ **AS 4666:2012 Section 5.3.7** GLASS: A visual inspection shall be conducted for Scratches, Blemishes, Marks and Inclusions. Refer to AS 4666, Table 5.5 and Table 5.6 **Scratches, Marks and Inclusions, etc Check ☐ Pass:** | **Scratches, Marks and Inclusions, etc Check ☐ Fail:** **Notes:** 100% inspection all glazing materials. | **Signature.** *Activity Completed* ☐ **Yes** ☐ No

The rest of this page has intentionally been left blank.

NORTHERN GLASS SOLUTIONS

PAS-Mark

COMPONENT CHECKED:	Spacer Bar & Connectors

Check List Item No.	Standard requirement to be verified.
4. 4.1	☐ **AS 4666:2012 (Section 5.4.1 and 5.4.7.1 Spacer Bar Dimensional Properties)** SPACER BAR: A permanent record shall be kept identifying stock used to manufacture a customer order.

Spacer Bar Manufacturer:	
Batch Number:	
Product Name or Code:	
Date of Receipt:	
Spacer Bar Size: L x W x H	
Spacer Bar Wall Thickness:	
Spacer Bar Quantity:	
Spacer Bar Grade:	
Spacer Bar Finish/Colour:	

Spacer Bar Record Maintained ☐ **Pass:**	**Spacer Bar Record Maintained** ☐ **Fail:**
Notes: One check each production shift. Spacer materials, size, quantity, grade, type of finish/colour, wall thickness.	**Signature.**

Activity Completed ☐ **Yes** ☐ No (Records maintained for 5.4.1)

4.2	☐ **AS 4666:2012 (Section 5.4.2)** SPACER BAR: A permanent record shall be kept identifying stock used to manufacture a customer order, it shall be traceable back to the supplier.

Customer Stock Record Maintained ☐ **Pass:**	**Customer Stock Record Maintained** ☐ **Fail:**
Notes: One check each customer order produced.	**Signature.**

Activity Completed ☐ **Yes** ☐ No (Records maintained for 5.4.2)

4.3	☐ **AS 4666:2012 (Section 5.4.3.1)** RIGID SPACER BAR TYPE: Spacer bar material checked for ☐ Straightness, ☐ Dents or ☐ Marks, ☐ Fracture of seams, ☐ Consistency of colour or applied finish.

Straightness, Dents, Marks, etc Check ☐ **Pass:**	**Straightness, Dents, Marks, ect Check** ☐ **Fail:**
Notes: One check each production shift.	**Signature.**

Activity Completed ☐ **Yes** ☐ No

NORTHERN GLASS SOLUTIONS

PAS-Mark

4.4	☐ **AS 4666:2012 (Section 5.4.4 and 5.4.5)** JOINERS – CORNER KEYS AND STRAIGHT LINE CONNECTORS: Checked for ☐ Compatibility with spacer bar being used, ☐ Align correctly, ☐ Tight and rigid join. **Compatibility, Alignment, Joint Check Completed.** ☐ **Pass:** | **Compatibility, Alignment, Joint Check Completed.** ☐ **Fail:** **Notes:** One check each production shift. | **Signature.** *Activity Completed* ☐ **Yes** ☐ No
4.5	☐**AS 4666:2012 (Section 5.4.6, Appendix I)** SPACER BAR CLEANLINESS: A visual inspection shall be conducted to ensure the spacer bar is free from Dirt, Oil, Grease or other Contaminants. **Spacer Bar Cleanliness Check** ☐ **Pass:** | **Spacer Bar Cleanliness Check** ☐ **Fail:** **Notes:** One check each production shift. | **Signature.** *Activity Completed* ☐ **Yes** ☐ No (Records to be maintained if spacer bar is discarded or returned to the supplier)
4.6	☐**AS 4666:2012 (Section 5.4.7.1)** DIMENSIONAL PROPERTIES SPACER BARS: The dimensional properties of the spacer bars shall be in compliance with the manufacturers specifications. **Spacer Bar Dimensional Check** ☐ **Pass:** | **Spacer Bar Dimensional Check** ☐ **Fail:** **Notes:** One check each production shift. | **Signature.** *Activity Completed* ☐ **Yes** ☐ No
4.7	☐**AS 4666:2012 (Section 5.4.8)** SPACER BAR POST ASSEMBLY INSPECTION: Evidence of material splitting, tearing or flare out on bent corners shall automatically render an assembled frame unfit for use. **Spacer Bar Post Assembly Check** ☐ **Pass:** | **Spacer Bar Post Assembly Check** ☐ **Fail:** **Notes:** One check each production shift. | **Signature.** *Activity Completed* ☐ **Yes** ☐ No

The rest of this page has intentionally been left blank.

COMPONENT CHECKED:	Desiccant

Check List Item No.	Standard requirement to be verified.
5. 5.1	☐ **AS 4666:2012 (Section 5.5.2 and 5.5.8 Shelf Life)** DESICCANT – ORIGIN AND COMPLIANCE WITH ORDER: A permanent record shall be kept identifying stock used to manufacture a customer order. **Desiccant Manufacturer:** **Batch Number:** **Product Name or Code:** **Desiccant Molecular Sieve:** **Date of Receipt:** **Product Expiry Date:** **Desiccant Material Record Maintained** ☐ **Pass:** / **Desiccant Material Record Maintained** ☐ **Fail:** **Notes:** One check each production shift. Desiccant materials expiry date, molecular sieve. / **Signature.** *Activity Completed* ☐ **Yes** ☐ No (Records maintained for 5.5.2 – NOTE: 5.5.8 Desiccant material exceeding its specified in use by date shall be discarded - Records to be maintained)
5.2	☐**AS 4666:2012 (Section 5.5.3)** DESICCANT TRACEABILITY. A permanent record shall exist to identify desiccant used in fulfilling each customer's order, it shall be traceable back to the supplier. **Desiccant Filling Record Maintained For Customer Order.** ☐ **Pass:** / **Desiccant Filling Record Maintained For Customer Order.** ☐ **Fail:** **Notes:** One check each production shift. / **Signature.** *Activity Completed* ☐ **Yes** ☐ No (Records maintained for 5.5.3)
5.3	☐**AS 4666:2012 (Section 5.5.5)** DESICCANT EFFECTIVENESS/FIT FOR PURPOSE: Prior to each new day's production run the manufacturers specification to test the desiccant is effective - fit for purpose, is undertaken and the test result has been recorded. **Desiccant: Effectiveness/Fit for Purpose** ☐ **Pass:** / **Desiccant: Effectiveness/Fit for Purpose** ☐ **Fail:** **Notes:** One check each production shift. / **Signature.** *Activity Completed* ☐ **Yes** ☐ No (Records maintained for 5.5.5)
5.4	☐**AS 4666:2012 (Section 5.5.6, Appendix J)** DESICCANT VOLUME MEASUREMENT: Adequate volume of desiccant has been employed in the spacer bar cavity. **Volume of Desiccant** ☐ **Pass:** / **Volume of Desiccant** ☐ **Fail:** **Notes:** One check each production shift. / **Signature.** *Activity Completed* ☐ **Yes** ☐ No

5.5	☐**AS 4666:2012 (Section 5.5.7)** DESICCANT EXPOSURE: Desiccant exposure to atmosphere *(Maximum 2 hours, recommended 40 minutes)*. Time of filling and time of assembly is recorded? **Desiccant Exposure** ☐ **Pass:** | **Desiccant Exposure** ☐ **Fail:** **Notes:** One check each customer order or every two hours of each production shift, whichever is the lesser. | **Signature.** *Activity Completed* ☐ **Yes** ☐ No (Records maintained for 5.5.7)
5.6	☐**AS 4666:2012 (Section 5.5.9)** DESICCANT MATERIAL SUITABILITY TO GASSING OF INSULATING GLASS UNITS: The desiccant material in use is compatible with the gas type to be used in the assembly of the IGU. ☐ **Not Applicable to the product being manufactured – Air Filled Cavity** or **Desiccant Suitability With Gas In Use** ☐ **Pass:** | **Desiccant Suitability With Gas In Use** ☐ **Fail:** **Notes:** One check each customer order. | **Signature.** *Activity Completed* ☐ **Yes** ☐ No

The rest of this page has intentionally been left blank.

COMPONENT CHECKED:	Sealants

Check List Item No.	Standard requirement to be verified.
6. 6.1	☐ **AS 4666:2012 (Section 5.6.1 and 5.6.10.1 Shelf Life)** SEALANT – ORIGIN AND COMPLIANCE WITH ORDER: A permanent record shall be kept identifying stock used to manufacture a customer order. **Sealant Manufacturer:** **Batch Number:** **Product Name or Code:** **Date of Receipt:** **Product Expiry Date:** **Sealant Material Record Maintained** ☐ **Pass:** / **Sealant Material Record Maintained** ☐ **Fail:** **Notes:** One check each production shift. Desiccant materials expiry date, molecular sieve. **Signature.** *Activity Completed* ☐ **Yes** ☐ No (Records maintained for 5.6.1 – NOTE: 5.6.10.1 If sealant in use by date is reached prior to use the manufacturer shall be contacted for further instructions all subsequent actions shall be recorded.)
6.2	☐**AS 4666:2012 (Section 5.6.2)** Traceability of sealants used in fulfilling a customer order. (Two part sealant mix shall record details on each component part used in the mix). PRIMARY SEALANT: A permanent record shall be kept identifying stock used to manufacture a customer order it shall be traceable back to the supplier. **Primary Sealant Record Maintained** ☐ **Pass:** / **Primary Sealant Record Maintained** ☐ **Fail:** **Notes:** One check each production shift. Sealant Manufacturer/Type – Batch Number – Expiry Date **Signature.** *Activity Completed* ☐ **Yes** ☐ No (Records maintained for 5.6.2) ☐SECONDARY SEALANT: A permanent record shall be kept identifying stock used to manufacture a customer order it shall be traceable back to the supplier. **Secondary Sealant Record Maintained** ☐ **Pass:** / **Secondary Sealant Record Maintained** ☐ **Fail:** **Notes:** One check each production shift. Sealant Manufacturer/Type – Batch Number – Expiry Date **Signature.** *Activity Completed* ☐ **Yes** ☐ No (Records maintained for 5.6.2)

6.3

☐**AS 4666:2012 (Section 5.6.4)**
SEALANTS: Minimum sealant dimensions verified to Table 5.7, AS 4666.

Type of Sealed Unit Checked - ☐ Dual Seal – ☐ Single Seal	
Minimum Sealant Dimensions ☐ Pass:	**Minimum Sealant Dimensions ☐ Fail:**
Notes: One check each production shift. Random samples selected in numbers as specified in Table 6.1, AS 4666, from different manufacturing lots and from different insulating glass unit makeups.	**Signature.**

Table 6.1 – AS 4666

Type	Sealant	A mm	B mm	C mm	D mm
Single seal units					
 where A = total depth of seal B = beneath spacer depth C = thickness of seal	Hot melt	10	5	1.5	N/A
	Polysulphide	8	4	1.5	N/A
	Polyurethane	8	4	1.5	N/A
	Silicone	N/A	N/A	N/A	N/A
Dual seal units					
 where A = total depth of seal B = beneath spacer depth C = primary seal depth D = primary seal thickness	Hot melt	10	4	3.5	0.25
	Polysulphide	10	4	3.5	0.25
	Polyurethane	10	4	3.5	0.25
	Silicone	10	4	3.5	0.25

NOTES:

Activity Completed ☐ **Yes** ☐ No

6.4

☐**AS 4666:2012 Section 5.6.5**
SEALANT COMPATABILITY WITH GLASS: The sealant material/s and glazing materials have been confirmed as compatible and approved for use.

Sealant/Glass Compatibility ☐ Pass:	**Sealant/Glass Compatibility ☐ Fail:**
Notes: One check each production shift.	**Signature.**

Activity Completed ☐ **Yes** ☐ No

6.5

☐**AS 4666:2012 Section 5.6.6**
SEALANT ADHESION: To the glass surface and spacer bar. (Section 5.6.6 & Appendix K) Records to be maintained.

Secondary Adhesion ☐ Pass:	**Secondary Adhesion ☐ Fail:**
Notes: One check each production shift.	**Signature.**

Activity Completed ☐ **Yes** ☐ No (Records maintained for 5.6.6)

NORTHERN GLASS SOLUTIONS

PAS-Mark

6.6	☐ **AS 4666:2012 Section 5.6.7** MIX RATIO: Where two part secondary sealants are used the mix ratio shall be tested. (Section 5.6.7 & Appendix L) Records to be maintained. **Mix Ratio** ☐ **Pass:** / **Mix Ratio** ☐ **Fail:** **Notes:** One check each production shift. / **Signature.** *Activity Completed* ☐ **Yes** ☐ No (Records maintained for 5.6.7)
6.7	☐ **AS 4666:2012 Section 5.6.8** MIX HOMOGENEITY: (AS 4666:2012 Section 5.6.8 & Appendix M) Tested once per shift results to be recorded. **Mix Homogeneity** ☐ **Pass:** / **Mix Homogeneity** ☐ **Fail:** **Notes:** One check each production shift. / **Signature.** *Activity Completed* ☐ **Yes** ☐ No (Records maintained for 5.6.8)
6.8	☐ **AS 4666:2012 Section 5.6.9** SEALANT CURE RATE: (Section 5.6.9 & Appendix N) The cure rate of single or secondary sealants shall be tested. Records to be maintained. **Reading 1** / **Reading 2** / **Reading 3** / **Reading 4** / **Reading 5** **Average Initial Hardness:** **Sealant Cure Rate** ☐ **Pass:** / **Sealant Cure Rate** ☐ **Fail:** **Notes:** One check each production shift. / **Signature.** *Activity Completed* ☐ **Yes** ☐ No (Records maintained for 5.6.9)
6.9	☐ **AS 4666:2012 (Section 5.6.10.2 Storage) Sealant** materials are stored in accordance with the manufacturers specification. **Sealant Material/s Storage Check** ☐ **Pass:** / **Sealant Material/s Storage Check** ☐ **Fail:** **Notes:** One check each production shift. / **Signature.** *Activity Completed* ☐ **Yes** ☐ No

The rest of this page has intentionally been left blank.

COMPONENT CHECKED:	Gas

Check List Item No.	Standard requirement to be verified.
7. 7.1	☐**AS 4666:2012** GASSING OF UNITS: **(Section, 5.7.1, Origin and Compliance of Order), (5.7.3, Gas Type)** A permanent record shall be kept identifying the specific gas used to manufacture a customer order.

Gas Manufacturers Details:	
Type of Gas:	☐ **Argon** ☐**Krypton** ☐ **Carbon Dioxide** ☐ **Blend** (Specific % and Composition) ☐ **Sulphur Hexa Fluoride**
Date of Receipt:	

Gas Record Maintained ☐ **Pass:**	**Gas Record Maintained** ☐ **Fail:**
Notes: One check each production shift.	**Signature.**

Activity Completed ☐ **Yes** ☐ No (Records maintained for 5.7.1)

7.2	☐**AS 4666:2012** GASSING OF UNITS: **(Section, 5.7.2 Traceability)** A permanent record shall exist to identify specific gas used in fulfilling each customer's order, it shall be traceable back to the supplier.

Gas Filling Record Maintained For Customer Order. ☐ **Pass:**	**Gas Filling Record Maintained For Customer Order.** ☐ **Fail:**
Notes: One check each production shift.	**Signature.**

Activity Completed ☐ **Yes** ☐ No (Records maintained for 5.7.2)

7.3	☐**AS 4666:2012** GASSING OF UNITS: **(Section, 5.7.5 Compatibility With Desiccant)** The Pore Size of the desiccant shall be smaller than the Molecular Sieve of the specific gas being introduced into the IGU.

Desiccant Pore Size verified as smaller than Gas Molecular Sieve Size. ☐ **Pass:**	**Desiccant Pore Size verified as smaller than Gas Molecular Sieve Size.** ☐ **Fail:**
Notes: One check each production shift.	**Signature.**

Activity Completed ☐ **Yes** ☐ No

7.4	☐**AS 4666:2012** GASSING OF UNITS: **(Section, 5.7.6, Volume/Pressure)** The introduced specific gas fill shall be a minimum 90%

GAS Fill is verified as 90% of IGU Cavity Volume: ☐ **Pass:**	**GAS Fill is verified as 90% of IGU Cavity Volume:** ☐ **Fail:**
Notes: One check each production shift. May be calculated or measured in accordance with Appendix O	**Signature.**

Activity Completed ☐ **Yes** ☐ No

The rest of this page has intentionally been left blank.

COMPONENT CHECKED:	Compliance Markings

Check List Item No.	Standard requirement to be verified.
8. 8.1	AS 4666:2012 Section 4 Marking COMPLIANCE MARKING is in accordance with AS 4666: All insulated glazing units shall be clearly marked prior to final inspection/shipment. Marking shall include the following details as a minimum. ☐Company Name or Logo ☐Manufacturing site identifier (CSi Id 7709) ☐Manufacturing Standard: AS 4666 ☐Date of manufacture (Month and Year) *(CSi require both details to be shown for traceability of manufacturing time period)* **Compliance Markings** ☐ **Pass:** / **Compliance Markings** ☐ **Fail:** **Notes: Visual Inspection.** / **Signature.** Compliance markings requirements for safety glazing materials used in the manufacture of the IGU shall also be met. (For example: AS/NZS 2208 Safety glazing materials in buildings shall be marked in compliance with that standard). **Notes:** 100% check each production shift. *Activity Completed* ☐ **Yes** ☐ No
8.2	The Insulated glazing units shall be identified by a work order/customer order label affixed to the finished product. *Activity Completed* ☐ **Yes** ☐ No

COMPONENT CHECKED:	Final Product Check

Check List Item No.	Standard requirement to be verified.
9. 9.1	**Completed Unit Final Checks** ☐**AS 4666:2012 Section 5.8.2 Test Format**. Prior to shipment random samples selected in the numbers specified in Table 6.1 shall be tested in accordance with Clause 2.2 of AS 4666. Where practicable samples shall be selected from different manufacturing lots and from different insulating glass unit make ups. Any non-conforming product shall be rectified or replaced. (Records maintained for 5.8.2 if non-conforming product is found, another product shall be inspected in its place) *Activity Completed* ☐ **Yes** ☐ No
9.2	☐**AS 4666:2012 Section 5.8.3** Sealant Cured. **Sealant Cure Check** ☐ **Pass:** / **Sealant Cure Check** ☐ **Fail:** **Notes: Visual Inspection, mechanical hardness check.** Check Sealant Hardness against manufacturers specification for a fully cured sealant. No sign of uncured sealant on units ready for shipment. **Signature.** *Activity Completed* ☐ **Yes** ☐ No
9.3	☐**AS 4666:2012 Section 5.8.4** Dimensional Properties: *(Height x Width, Squareness, Flatness).* Refer to Sections 5.8.4.2, - 5.8.4.3, - 5.8.4.4 and Table 5.8 **Dimensional Properties Check** ☐ **Pass:** / **Dimensional Properties Check** ☐ **Fail:** **Notes: Visual Inspection** Random samples selected in numbers as specified in Table 6.1, AS 4666, from different manufacturing lots and from different insulating glass unit makeups. **Signature.** *Activity Completed* ☐ **Yes** ☐ No
9.4	☐**AS 4666:2012 Section 5.8.5** Uniformity of Spacer Depth **Uniformity of Spacer Depth Check** ☐ **Pass:** / **Uniformity of Spacer Depth Check** ☐ **Fail:** **Notes: Visual Inspection** Minimum sealant depth given in AS 4666, Table 5.7. Random samples selected in numbers as specified in Table 6.1, AS 4666, from different manufacturing lots and from different insulating glass unit makeups. **Signature.** *Activity Completed* ☐ **Yes** ☐ No
9.5	☐**AS/NZS 4666:2012 Section 5.8.6** Voids in Sealants **Voids in Sealants Check** ☐ **Pass:** / **Voids in Sealants Check** ☐ **Fail:** **Notes: Visual Inspection.** Random samples selected in numbers as specified in Table 6.1, AS 4666, from different manufacturing lots and from different insulating glass unit makeups. **Signature.** *Activity Completed* ☐ **Yes** ☐ No

9.6	☐**AS 4666:2012 Section 5.8.7** Glass Alignment/Offset **Glass Alignment/Offset Check** ☐ **Pass:** **Notes: Visual Inspection.** Random samples selected in numbers as specified in Table 6.1, AS 4666, from different manufacturing lots and from different insulating glass unit makeups. **Glass Alignment/Offset Check** ☐ **Fail:** **Signature.** *Activity Completed* ☐ **Yes** ☐ No
9.7	☐**AS 4666:2012 Section 5.8.9 Cleanliness** **Sealant Cleanliness Check** ☐ **Pass:** **Notes: Visual Inspection.** On the face of the glazing No protrusion past the sealant and spacer depth shall be allowed. Ayn sealant shall be not greater than 1 mm high from the face of the glazing. On the edge of the unit The sealant shall be uniform with no voids and shall be not greater than 2 mm proud of the edge of the glazing along the edges and not greater than 3 mm on any corner. From a corner point, the corner shall include 20 mm in each direction. **Sealant Cleanliness Check** ☐ **Fail:** **Signature.** *Activity Completed* ☐ **Yes** ☐ No
9.8	☐**AS 4666:2012 Section 5.8.10 Marks/Scratches and Inclusions** **Marks/Scratches and Inclusions Check** ☐ **Pass:** **Notes: Visual Inspection.** Each piece of glazing material in the completed IGU may contain scratches, blemishes and inclusions, Refer to Table 5.5, AS 4666. A finished IGU may have twice the amount given in Table 5.5, however the restriction for each piece of glazing material given in Table 5.5 shall not be exceeded. **Marks/Scratches and Inclusions** ☐ **Fail:** **Signature.** *Activity Completed* ☐ **Yes** ☐ No
9.9	☐**AS 4666:2012** MOISTURE CONTENT: **Section 5.8.11 & Appendix P** Moisture content (Dew Point Test) shall be conducted on units from the previous day's production lot. **Moisture Content Check** ☐ **Pass:** **Notes: Visual Inspection, Test to Appendix P.** Random samples selected in numbers as specified in Table 6.1, AS 4666, from different manufacturing lots and from different insulating glass unit makeups. **Moisture Content Check** ☐ **Fail:** **Signature.** *Activity Completed* ☐ **Yes** ☐ No
9.10	☐**AS 4666:2012 Section 5.8.12 (All)** **Storage and Handling Check** ☐ **Pass:** **Notes: Visual Inspection.** Storage and handling of uncured units within the manufacturing environment shall be in accordance with the stated requirements of Sections 5.8.12.1 - Support, 5.8.12.2 - Angle and, 5.8.12.3 – Spacing/Interleaving. Lifting large units is conducted by attaching the lifting device to the thickest glazing material face of the IGU. **Storage and Handling Check** ☐ **Fail:** **Signature.** *Activity Completed* ☐ **Yes** ☐ No

EQUIPMENT AVAILABILITY - CONFIRMATION CHECK:

Check List Item No.	Standard requirement to be verified.
10. 10.1	☐**AS 4666:2012 Appendix A** DETERMINATION OF DIMENSIONAL PROPERTIES: Do the IGU Line Operators have access to the following ***Mandatory Equipment** for determination of dimensional properties of insulating glass units? 1☐Point Micrometre*- 0.01mm 2☐Plate Micrometre*- 0.01mm 3☐ Vernier Calliper*- 0.01mm (*Digital Vernier Caliper acceptable*) 4☐150mm Steel Rule or Steel Tapered Rule*- 0.5mm 5☐Standard Measuring Tape*- 1.0mm 6☐Straight Edge* **Mandatory Equipment Check** ☐ **Pass:** / **Mandatory Equipment Check** ☐ **Fail:** **Notes:** Monitoring and measurement devices shall be calibrated, identified, protected from adjustments, damage and deterioration during handling, maintenance and storage. / **Signature.** *Activity Completed* ☐ **Yes** ☐ No
10.2	Do the IGU Line Operators have access to any or all of the following additional equipment to undertake product compliance checks in accordance with AS 4666, Section 5, Manufacturing and Periodic Testing? 1☐Durometer Type A2 – 0 to 100 increments 2☐Teflon Mould *(Length 127mm x Width 38mm x Height 6mm*) 3☐Digital Thermometer 4☐Stopwatch 5☐Barometric Pressure - Humidity/Temperature Gauge/Datalogger 6☐Dry Ice Maker (*Snowpac Device*) 7☐Crucible to hold dry ice 8☐Calculator 9☐Digital Scales 10☐One litre beaker with sight scale in 50ml graduations 11☐Handheld ultra-violet light source 12☐Delta T test kit 13☐Sparklite (*Used to test IG gas concentration*) 14☐Non-powdered latex gloves 15☐Disposable paper towel **Additional Equipment Check** ☐ **Pass:** / **Additional Equipment Check** ☐ **Fail:** **Notes:** Monitoring and measurement devices shall be calibrated, identified, protected from adjustments, damage and deterioration during handling, maintenance and storage. / **Signature.** *Activity Completed* ☐ **Yes** ☐ No
10.3	The measuring equipment is calibrated to be within the stated tolerance of 0.01mm and the equipment is functional? **Equipment Calibrated and Functional** ☐ **Pass:** / **Equipment Calibrated and Functional** ☐ **Fail:** **Notes:** Monitoring and measurement devices shall be calibrated, identified, protected from adjustments, damage and deterioration during handling, maintenance and storage. **Records are to be maintained.** / **Signature.** *Activity Completed* ☐ **Yes** ☐ No

The rest of this page has intentionally been left blank.