	3 days	7 days	14 days	28 days	56 days	100 days	
W./F.A.	-0.17	-0.12	0.06	-0.14	-0.1	-0.21	
W./C.A.	-0.31	-0.15	-0.36	-0.19	-0.01	-0.42	
F.A./C.A.	-0.02	0.13	-0.37	-0.02	0.15	-0.1	Correlation
C.A./C.	-0.71	-0.72	-0.34	-0.64	-0.62	-0.44	1.0
F.A./C.	-0.69	-0.64	-0.42	-0.62	-0.65	-0.47	
W./C.	-0.76	-0.69	-0.53	-0.65	-0.7	-0.56	0.5
Fine agg.	-0.21	-0.17	-0.39	-0.15	-0.22	-0.19	0.0
Coarse agg.	-0.19	-0.43	0.28	-0.11	-0.47	-0.04	0.0
Superplast.	0.63	0.74	0.26	0.18	0.56	0.65	-0.5
Water	-0.5	-0.53	-0.3	-0.38	-0.36	-0.53	-0.5
Fly ash	-0.1	0.23	-0.06	-0.27	-0.53	0	-1.0
B.F.S.	0.02	0	0.16	0.13	0.67	0.25	
Cement	0.78	0.78	0.47	0.66	0.64	0.47	
	mpa	mpa	mpa	mpa	mpa	тра	