Table 1: Battery dataset summary grouped by electrode chemistry. LFP | NMC / NCA | LCO | LCO + NMC | LFP + NCA + NMC | Na-ion | Zn-MnO_2

Name	Number of Cells	Positive Electrode	Negative Electrode	Nominal Capacity (Ah)	Temperature (°C)
HUST (18650 cylindrical)	77	**LFP** lithium-iron-phosphate	Graphite	1.1	30
MATR (18650)	169	**LFP** $LiFePO_4$	Graphite	1.1	30
CALB	27	**NMC**	Graphite	58	0, 25, 35, 45
ISU (502030 Li-polymer)	240	**NMC** lithium nickel manganese cobalt oxide	Graphite	0.25	30
MICH_EXP (pouch)	12	**NMC** NMC111	Graphite	5.0	-5, 25, 45
MICH	40	**NMC** NMC111	Graphite	2.36	25, 45
RWTH	48	**NMC** (lithium nickel manganese cobalt oxide)	Carbon	3	25
SDU (18650)	86	**NMC**	Graphite	2.4	25
STANDFORD (18650)	41	**NMC** $LiNi_{0.5}Mn_{0.3}Co_{0.2}O_2$	Graphite	0.24	30
STANDFORD 2 (18650)	181	**NMC** $LiNi_{0.5}Mn_{0.3}Co_{0.2}O_2$	Graphite	0.24	30
XJTU	23	**NMC** $LiNi_{0.5}Co_{0.2}Mn_{0.3}O_2$	Graphite	2	20
TONGJI (18650 cylindrical)	108	**NCA** / **NMC** $Li_{0.86}Ni_{0.86}Co_{0.11}Al_{0.03}O_2$ / $Li_{0.84}(Ni_{0.83}Co_{0.11}Mn_{0.07})O_2$ / NCA + NMC blend	Graphite / Graphite + 2 wt.% Si	2.5 and 3.5	multiple
CALCE	13	**LCO** $LiCoO_2$	Graphite	1.1	25
HNEI	—	**LCO + NMC** $LiCoO_2$ and $LiNi_{0.4}Co_{0.4}Mn_{0.2}O_2$	Graphite	2.8	25
UL (18650)	10	**LCO + NMC** $LiCoO_2$ and $LiNi_{0.4}Co_{0.4}Mn_{0.2}O_2$	Graphite	3.4	23
SNL (18650)	52	**LFP + NCA + NMC** $LiFePO_4$ / $LiNi_{0.81}Co_{0.14}Al_{0.05}O_2$ / $LiNi_{0.84}Mn_{0.06}Co_{0.1}O_2$	Graphite	1.1 3.2 3.0	15, 25, 35
NA-ION (18650)	31	**Na-ion**	—	1.0	25
ZN-COIN	95	**Zn-MnO_2** manganese dioxide (MnO_2) cathode	Zinc	10	25