

Direct gap of the lowest-N subspace: pristine beryllenes
(a) α-beryllene
N = 2: sampled min 1.13 meV
(b) β-beryllene
N = 4: sampled min 0.898 meV
(c) trilayer cubic beryllene
N = 6: sampled min 0.735 meV
Γ
0.5
0.0
−0.5
k_2 (units of $\vec{b}_2$)
k_1 (units of $\vec{b}_1$)
10^1
10^0
10^{-1}
10^{-2}
$E_{N+1} - E_N$ (eV)
TRIM
refined minima and their symmetry images