

Energy versus energy cutoff for g-Beryllene

