


Sample: T3SG2
 Operator: LvdM, ChemEng, Stb Uni
 Submitter: Rebekah Haschick, BotZoo, Dr Ndlovu
 File: C:\...\RHASCH~1\005-960.SMP

Test Number: 3
 Analyzed: 2026/06/26 10:21:16PM
 Reported: 2026/06/29 11:05:06PM
 Background: 2026/06/26 9:53:13PM

Model: (1.520, 0.1000000), 1.331
 Material: Sand / Water
 Background: Water RI 1.331
 Smoothing: Medium

Comments: 0.0005% TSPP. Initial obsc = 10.1%

Combined Report



Summary Report

Analysis Conditions

FlowRate: 12.0 l/m
 Circulation time: 60 sec

Ultrasonic intensity: 60 %
 Ultrasonic time: 75 sec

Sample

Sample Concentration: 0.00423 %
 Obscuration: 11.9 %

Volume Distribution Arithmetic Statistics

		Std Dev of 3			Std Dev of 3
Mean	51.79	3.185	Mode	212.6	96.06
Median	16.76	1.023			

Selected Sizes

Diameter (µm)	Percent Finer
100.0	82.4
50.00	69.2
20.00	52.5
10.00	41.4
1.000	5.0

Peaks

Peak Number	% of Dist.*	% of Dist. Std Dev of 3	Mean	Mean Std Dev of 3	Median	Median Std Dev of 3	Mode
1	6.2	N/A	0.828	N/A	0.818	N/A	0.799
2	34.0	N/A	4.020	N/A	3.561	N/A	4.005
3	11.9	N/A	13.60	N/A	13.22	N/A	12.67
4	32.4	N/A	53.61	N/A	48.01	N/A	50.42
5	15.4	N/A	203.1	N/A	201.2	N/A	212.6

* Peaks must comprise at least 5.00 % of the distribution.

Sample: T3SG2
Operator: LvdM, ChemEng, Stb Uni
Submitter: Rebekah Haschick, BotZoo, Dr Ndlovu
File: C:\...\RHASCH~1\005-960.SMP

Test Number: 3
Analyzed: 2026/06/26 10:21:16PM
Reported: 2026/06/29 11:05:06PM
Background: 2026/06/26 9:53:13PM

Model: (1.520, 0.1000000), 1.331
Material: Sand / Water
Background: Water RI 1.331
Smoothing: Medium

Comments: 0.0005% TSPP. Initial obsc = 10.1%

Report by Size Table

Low Diameter (μm)	Cumulative Volume Finer (Percent)	Low Diameter (μm)	Cumulative Volume Finer (Percent)	Low Diameter (μm)	Cumulative Volume Finer (Percent)	Low Diameter (μm)	Cumulative Volume Finer (Percent)
300.000	99.9	60.000	73.1	8.000	38.2	0.900	4.0
250.000	97.3	50.000	69.2	7.000	36.1	0.800	2.9
200.000	92.1	40.000	64.5	6.000	33.5	0.700	1.6
150.000	86.7	30.000	58.9	5.000	30.2	0.600	0.5
100.000	82.4	25.000	55.9	4.000	25.6	0.500	0.1
90.000	80.9	20.000	52.5	3.000	19.7		
80.000	78.9	10.000	41.4	2.000	12.7		
70.000	76.3	9.000	39.9	1.000	5.0		



Micromeritics Instrument Corporation

Saturn DigiSizer 5200 V1.12

Saturn DigiSizer 5200 V1.12

5200 LSHU V2.01 S/N 216

Page 3

Sample: T3SG2
Operator: LvdM, ChemEng, Stb Uni
Submitter: Rebekah Haschick, BotZoo, Dr Ndlovu
File: C:\...\RHASCH~1\005-960.SMP

Test Number: 3
Analyzed: 2026/06/26 10:21:16PM
Reported: 2026/06/29 11:05:06PM
Background: 2026/06/26 9:53:13PM

Model: (1.520, 0.1000000), 1.331
Material: Sand / Water
Background: Water RI 1.331
Smoothing: Medium

Comments: 0.0005% TSPP. Initial obsc = 10.1%

Report by Volume Percent


Low Diameter (μm)	Cumulative Volume Finer (Percent)	Low Diameter (μm)	Cumulative Volume Finer (Percent)	Low Diameter (μm)	Cumulative Volume Finer (Percent)
181.681	90.0	16.759	50.0	1.647	10.0

Sample: T3SG2
Operator: LvdM, ChemEng, Stb Uni
Submitter: Rebekah Haschick, BotZoo, Dr Ndlovu
File: C:\...\RHASCH~1\005-960.SMP

Test Number: 3
Analyzed: 2026/06/26 10:21:16PM
Reported: 2026/06/29 11:05:06PM
Background: 2026/06/26 9:53:13PM

Model: (1.520, 0.1000000), 1.331
Material: Sand / Water
Background: Water RI 1.331
Smoothing: Medium

Comments: 0.0005% TSPP. Initial obsc = 10.1%




Sample: T3SG2
Operator: LvdM, ChemEng, Stb Uni
Submitter: Rebekah Haschick, BotZoo, Dr Ndlovu
File: C:\...\RHASCH~1\005-960.SMP

Test Number: 3
Analyzed: 2026/06/26 10:21:16PM
Reported: 2026/06/29 11:05:06PM
Background: 2026/06/26 9:53:13PM

Model: (1.520, 0.1000000), 1.331
Material: Sand / Water
Background: Water RI 1.331
Smoothing: Medium

Comments: 0.0005% TSPP. Initial obsc = 10.1%



Sample: T3SG2
 Operator: LvdM, ChemEng, Stb Uni
 Submitter: Rebekah Haschick, BotZoo, Dr Ndlovu
 File: C:\...\RHASCH~1\005-960.SMP

Test Number: 3
 Analyzed: 2026/06/26 10:21:16PM
 Reported: 2026/06/29 11:05:06PM
 Background: 2026/06/26 9:53:13PM

Model: (1.520, 0.1000000), 1.331
 Material: Sand / Water
 Background: Water RI 1.331
 Smoothing: Medium

Comments: 0.0005% TSPP. Initial obsc = 10.1%

