An assessment of structural enthalpy and crystallization pathways of $Mg_{65}Zn_{30}Ca_5$ bulk metallic glass and amorphous films

Scott Gleason, David Miskovic, Nicholas Hamilton, Kevin Laws, Michael Ferry

UNSW Australia

School of Material Science and Engineering

August 7, 2017

ABSTRACT

The structural nature and thermal stability of amorphous alloys is highly dependent on the method by which they are produced, i.e. their relaxation rate upon cooling. Both bulk samples and metallic glass films of $Mg_{65}Zn_{30}Ca_5$ were produced by copper mold casting and direct current (DC) magnetron sputtering onto aluminium substrates, respectively. Comparisons between structural enthalpy, crystallization pathways, relaxation and crystallization kinetics of the bulk samples and films were examined by elevated temperature XRD and DSC. Compared with equivalent experiments on the bulk alloy, results for the thin films show distinct differences in structural enthalpy and deviations from the expected crystalline phase evolution, displaying minor peak shifts, failure of some phases to evolve, and variations in the evolution rates.

TABLE OF CONTENTS

1 INTRODUCTION

The structural nature and thermal stability of amorphous alloys is highly dependent on the method by which they are produced, i.e. their relaxation rate upon cooling. Both bulk samples and metallic glass films of $Mg_{65}Zn_{30}Ca_5$ were produced by copper mold casting and direct current (DC) magnetron sputtering onto aluminium substrates, respectively. Comparisons between structural enthalpy, crystallization pathways, relaxation and crystallization kinetics of the bulk samples and films were examined by elevated temperature XRD and DSC. Compared with equivalent experiments on the bulk alloy, results for the thin films show distinct differences in structural enthalpy and deviations from the expected crystalline phase evolution, displaying minor peak shifts, failure of some phases to evolve, and variations in the evolution rates.

Key sources [1, 2] [3]

2 METHOD

2.1 Master alloy

The master alloy of $Mg_{65}Zn_{30}Ca_5$ was produced using high-purity elements of Mg (99.85 wt%), Zn (99.995 wt%), and Ca (99.8 wt%). The alloy was prepared by induction melting in boron nitride coated graphite crucibles, purged with Ar (99.997 vol.% purity) five times, and protected with a circulating Ar atmosphere. Alloy homogeneity was ensured by heating and cooling through a cycle of 700°C, 385°C, 650°C, 385°C, 650°C to a casting temperature of 500 °C and 450°C for injection and gravity casting respectively. Bulk amorphous $Mg_{65}Zn_{30}Ca_5$ rods of $2.5mm$ diameter and plates of thickness of $XX\mu m$ were produced by copper mold injection casting. The $25.4mm$ diameter targets were prepared from a cylindrical copper mold gravity castings sectioned to thicknesses of $3.25mm$. All samples and targets were stored under Ar when not being examined or used.

2.2 DC magnetron sputtering

Films were produced from an in-house DC magnetron sputtering facility with Ar working gas (99.997 vol.% purity). The power was $15W$, typical voltage of $290-350V$, nominal chamber pressure of 1 bar, substrate temperature of 25°C, and Ar flow of 3.01 SCCM. Films were deposited directly onto to Al DSC lid substrates. Depositions were for a period of 35 minutes. Deposition rate was estimated at $1.2nm/s$.

2.3 Stylus profiler analysis

Nominal film thickness was measure by a stylus profiler (Dektak 2A, Bruker, Germany). A glass slide was placed under the substrates within the sputtering chamber, allowing the substrates to act as a mask. Profile measurements were taken by measuring the height difference between the bare glass and the film coated glass. This film thickness was used to estimate the sputter deposition rate.

2.4 EDS analysis

Alloy composition and homogeneity were confirmed by SEM-EDS (S3400, Hitachi, ?Japan?). Hyper-maps were collected with a accelerating voltage of $15 - 20kV$, and a probe current of $50\mu A$. (Conditions; counts were 5000 kps or better, dead time was less than 20 %, and working distance was 10mm).

2.5 DSC characterization

Isochronic DSC (204 F1 Phoenix, Netzsch, Selb, Germany) was carried out in Al crucibles under a protective Ar atmosphere (99.997 vol.% purity). Scans were performed at heating rates (βs) of 5 to $100K/min$.

Isothermal relaxation DSC was preformed by heating samples at $20K/min$ to the desired annealing temperature, holding for desired time, and Ar quenching to room temperature.

For annealed XRD the samples were heat treated in the DSC by heating to the desired temperature at $20K/min$ followed by Ar quenching to room temperature.

2.6 XRD characterization

Annealing XRD (Empyrean, PANalytical, Cu K_α X-ray source, $\lambda = 1.541\text{Å}$) was performed at room temperature. (Generator Voltage 45, Tube Current 40, Scan Step Size 0.0262606, Time per Step 397.29).

Dynamic XRD (D8, Bruker, Cu K_α X-ray source, $\lambda = 1.541\text{Å}$) was performed by raising temperature at a rate of $20K/min$ and performing scans *in situ*. The first scan was performed at $35°$C, then $75°$C, after which temperature was raised in $5K$ increments until reaching the peak temperature at $185°$C. The 2θ scans from $31 - 60°$ were completed within $1092sec$

(18min, 12sec) to minimise the effects of recrystallisation during the experiment. (Generator Voltage 45, Tube Current 100, Scan Step Size 0.02, Time per Step 134.4).

3 RESULTS

3.1 Alloy composition

From the 35 minute depositions a nominal film thickness of 2.5μm was obtained, giving a deposition rate of approximately 1.2nm/s. The temperature within the chamber was found to rise $3-4°$C, significantly less than the expected 20K suggested by similar setups [4].

EDS analysis shows good agreement in the nominal composition for both the bulk and film Mg$_{65}$Zn$_{30}$Ca$_5$, see Table 1.

EDS Analysis	Bulk (at%)	Film (at%)
Mg	64.85 ± 3.18	62.92 ± 3.24
Zn	29.55 ± 0.82	31.17 ± 0.95
Ca	5.60 ± 0.17	5.91 ± 0.19

Table 1: EDS composition of bulk and film Mg$_{65}$Zn$_{30}$Ca$_5$ in atomic weight percent.

3.2 DSC

3.2.1 Isochronic DSC

Isochronic DSC was performed on the bulk and film Mg$_{65}$Zn$_{30}$Ca$_5$ to examine the thermal properties. The bulk alloy was relaxed at 120$°$C for 10 minutes before DSC measurements to ensure the T_g was clearly visible. The film was not relaxed as unlike the bulk the lost in free volume from relaxation would be significant and make differences between the samples much more difficult to observe [source needed???].

The bulk Mg$_{65}$Zn$_{30}$Ca$_5$ was examined at heating rates (βs) of 5, 10, 15, 20, 30, 40, 60, 80, and 100 K/min to observe changes in the T_g and the T_xs with β. As expected greater β resulted in greater signal strength, exothermic peaks shifting to higher start temperatures, and an increase in thermal lag resulting in later exothermic finish temperatures and curve convolution. With this convolution the T_g and T_{x1} remained clearly visible for all βs, but $T_{x2,4,5}$ were only visible at low βs, and T_{x3} was not clear at any β, see Figure 1.

The film was examined at βs of 15, 20, 30, 40, 60, 80, and 100 K/min. The lower βs of 5 and 10 k/min were not utilised owing to the lower film signal compared to the bulk. The reduced signal was likely from the low mass of the film, about $\frac{1}{10}$ that of the bulk. The film showed the expected variable relationships with increasing β as observed in the bulk. The signal intensity increased at a compatible rate to bulk up until βs of 80 and 100 k/min. These final two βs showed great increases in the signal intensity. The exothermic peaks all convoluted together making many of the thermodynamic events difficult to observer. It also appeared that all exothermic events shifted to lower temperatures as compared to the bulk. The T_g and T_{x1}s were less defined than for the bulk, but could still be identified for all βs. For all βs the T_{x2-5} onsets could not be easily identified, see Figure 2.

3.2.2 Fragility

Using the isochronic DSC data the fragility (m) of the $Mg_{65}Zn_{30}Ca_5$ system could be established for both the bulk and film. Numerical solutions where used to fit the DSC variant of the Vogel–Fulcher–Tammann (VFT) relationship for β [5].

$$\beta^{-1} = \tau_0 \, e^{\left(\frac{D^* T_0}{T_g - T_0}\right)} \tag{1}$$

Where τ_0 is a pre-exponential factor, D^* is the liquid fragility parameter, and T_0 is the VFT temperature where the barrier to flow becomes infinite.

The m could then be calculated from Equation 2 [6, 7].

$$D^* = 590/(m-16) \tag{2}$$

Using these two equations for the bulk it was found $\beta^{-1} = 1.338E - 16e^{5274\left(\frac{1}{T-T_0}\right)}$ with an Adj. $R^2 = 0.972$. This gave a $D^* = 20.4$, and a $m = 44.9$. The film was fitted to $\beta^{-1} = 5.921E - 11e^{2766\left(\frac{1}{T-T_0}\right)}$ with a lower confidence of Adj. $R^2 = 0.861$, likely owing to the reduced number of data points. This gave a $D^* = 10.0$, and $m = 75.0$, see Figure 3.

3.3 DSC deconvolution

3.3.1 Onset determination

Both the bulk and film $Mg_{65}Zn_{30}Ca_5$ were examined at various DSC heating rates to observe changed in the T_g and T_x temperatures. As expected higher heating rates resulted endothermic peaks shifting to higher temperatures and curve convolution.

Numerical solutions were used to deconvolution the DSC data so the various T_x onsets could be determined. The results of the deconvolution are presented in Table 2 for the bulk and Table 3 for the film.

Heating Rate β K/min	T_g	T_{x1}	T_{x2}	T_{x3}	T_{x4}	T_{x5}
100	136.1	164.8	193.4	201.8	240.2	262.4
80	132.0	160.0	194.4	201.9	238.2	260.3
60	129.6	157.7	190.0	197.8	232.9	259.0
40	126.6	155.2	189.0	200.0	226.4	254.7
30	126.2	151.5	187.0	198.4	221.0	251.1
20	125.1	149.8	188.4	197.0	216.0	246.8
15	123.8	148.3	186.2	195.6	212.2	243.9
10	123.5	144.5	183.4	192.9	207.4	239.8
5	120.5	141.1	179.7	187.5	199.8	232.7

Table 2: Bulk $Mg_{65}Zn_{30}Ca_5$ alloy onset temperatures for the various DSC heating rates β. All temperatures are in $^\circ$C.

Heating Rate β K/min	T_g	T_{x1}	T_{x2}	T_{x3}	T_{x4}	T_{x5}
100	108.5	128.6		177.3		240.3
80	106.0	121.2		165.6		238.8
60	107.3	134.0		176.1		237.8
40	100.2	119.8		170.7		234.2
30	95.3	110.4		169.5		232.5
20	95.5	115.2		170.5		229.4
15	92.5	113.5		168.8		224.0

Table 3: Film $Mg_{65}Zn_{30}Ca_5$ alloy onset temperatures for the various DSC heating rates β. All temperatures are in $^\circ$C.

3.3.2 Reaction enthalpy

3.3.3 Relaxation enthalpy

3.4 XRD

3.4.1 Annealing XRD

3.4.2 Dynamic XRD

4 DISCUSSION

The use of a 60K DSC heating rate compared to the more commonly used 20K rate [sources] shifts peaks for the bulk $Mg_{65}Zn_{30}Ca_5$ alloy about 8 - 15 degrees higher. This higher heating rates were used because crystallization events for the films were difficult to differentiation at the lower heating rate. Films show little shift to high temperature peaks with increases heating rates, but large shifts with relaxation. Bulk show the opposite behaviour, larger peaks shifts with higher heating rates and little shift with relaxation.

5 CONCLUSIONS

6 ACKNOWLEDGEMENTS

Yu Wang for his assistance with XRD experimentation and Rietveld refinement.

7 REFERENCES

[1] Y. N. Zhang, G. J. Rocher, B. Briccoli, D. Kevorkov, X. B. Liu, Z. Altounian, and M. Medraj. Crystallization characteristics of the Mg-rich metallic glasses in the Ca-Mg-Zn system. *Journal of Alloys and Compounds*, 552:88–97, 2013.

[2] Yi-Nan Zhang, Dmytro Kevorkov, Xue Dong Liu, Florent Bridier, Patrice Chartrand, and Mamoun Medraj. Homogeneity range and crystal structure of the Ca2Mg5Zn13 compound. *Journal of Alloys and Compounds*, 523:75–82, 2012.

[3] Yi-Nan Zhang, Dmytro Kevorkov, Florent Bridier, and Mamoun Medraj. Experimental study of the Ca-Mg-Zn system using diffusion couples and key alloys. *Science and Technology of Advanced Materials*, 12(2):025003, 2011.

[4] J. Q. Wang, N. Chen, P. Liu, Z. Wang, D. V. Louzguine-Luzgin, M. W. Chen, and J. H. Perepezko. The ultrastable kinetic behavior of an Au-based nanoglass. *Acta Materialia*, 79(0):30–36, 2014.

[5] R. Busch, W. Liu, and W. L. Johnson. Thermodynamics and kinetics of the Mg65Cu25Y10 bulk metallic glass forming liquid. *Journal of Applied Physics*, 83(8):4134–4141, 1998.

[6] C. A. Angell and S. Borick. Specific heats Cp, Cv, Cconf and energy landscapes of glassforming liquids. *Journal of Non-Crystalline Solids*, 307 - 310:393–406, 2002.

[7] Shuai Wei, Zach Evenson, Isabella Gallino, and Ralf Busch. The impact of fragility on the calorimetric glass transition in bulk metallic glasses. *Intermetallics*, 55:138–144, 2014.

Figure 1: Bulk Mg$_{65}$Zn$_{30}$Ca$_5$ relaxed at 120 $^\circ$C for 10 minutes and heated at various heating rates. The insert stacks the differential scanning calorimetry (DSC) curves and labels the T_g and $T_x$es of the $100K/min$ sample.

ate_Bulk

Figure 2: Unrelaxed film Mg$_{65}$Zn$_{30}$Ca$_5$ heated at various heating rates. The insert stacks the DSC curves and labels the T_g and $T_x$es of the $100K/min$ sample.

ate_Film

Figure 3: Fitted fragility (m) for the Mg$_{65}$Zn$_{30}$Ca$_5$system obtained by DSC at various heating rates

m_mValue

Figure 4: DSC deconvolution for the bulk. From left to right, top to bottom, 5, 10, 15, 20, 30, 40, 60, 80, 100 K/min.

lk_Decon

Figure 5: DSC deconvolution for the film. From left to right, top to bottom, 15, 20, 30, 40, 60, 80, 100 K/min.

Figure 6: The T_gs and $T_x$es of the bulk $Mg_{65}Zn_{30}Ca_5$ at all heating rates.

Figure 7: The T_gs and $T_x$es of the bulk and film $Mg_{65}Zn_{30}Ca_5$ at all heating rates.

Figure 8: DSC onset temperatures and enthalpy of formation for the bulk and film.

Figure 9: XRD pattern for Bulk $Mg_{65}Zn_{30}Ca_5$ heated through several crystallization peaks identified from DSC

Figure 10: XRD pattern for Film $Mg_{65}Zn_{30}Ca_5$ heated through several crystallization peaks identified from DSC

./images/XRD_Dynamic_Bulk.png

(a)

./images/Bulk_Heated_XRD_Waterfall3D_Smooth2.png

(b)

amic_FullStack_Bulk

amic_WaterFall_Bulk

mic_Bulk

Figure 11: (a) Stacked X-ray diffraction (XRD) patterns from the incremental heating of bulk $Mg_{65}Zn_{30}Ca_5$. (b) Cascading XRD patterns from the incremental heating of bulk $Mg_{65}Zn_{30}Ca_5$.

(a)

(b)

Figure 12: (a) Stacked XRD patterns from the incremental heating of film $Mg_{65}Zn_{30}Ca_5$. (b) Cascading XRD patterns from the incremental heating of film $Mg_{65}Zn_{30}Ca_5$.