



Pole Shed App Ver 01 2022

**Job No.:** Andrew Griffiths

**Address:** 96 Jones Road, Grovetown, Blenheim 7273, New Zealand **Date:** 31/10/2024

**Latitude:** -41.495912

**Longitude:** 173.992544

**Elevation:** 2 m

**General Input**

Roof Live Load	0.25 KPa	Roof Dead Load	0.25 KPa	Roof Live Point Load	1.1 Kn
Snow Zone	N3	Ground Snow Load	0 KPa	Roof Snow Load	0 KPa
Earthquake Zone	3	Subsoil Category	D	Exposure Zone	B
Importance Level	1	Ultimate wind & Earthquake ARI	100 Years	Max Height	5.6 m
Wind Region	NZ2	Terrain Category	1.0	Design Wind Speed	42.77 m/s
Wind Pressure	1.1 KPa	Lee Zone	NO	Ultimate Snow ARI	50 Years
Wind Category	High	Earthquake ARI	100		

Note: Wind lateral loads are governing over Earthquake loads, So only wind loads are considered in calculations

**Pressure Coefficients and Pressures**

Shed Type = Gable Enclosed

For roof  $C_{p,i} = -0.3$

For roof  $C_{p,e}$  from 0 m To 5.6 m  $C_{p,e} = -0.9$   $p_e = -0.89$  KPa  $p_{net} = -0.89$  KPa

For roof  $C_{p,e}$  from 5.6 m To 11.2 m  $C_{p,e} = -0.5$   $p_e = -0.49$  KPa  $p_{net} = -0.49$  KPa

For wall Windward  $C_{p,i} = -0.3$  side Wall  $C_{p,i} = -0.3$

For wall Windward and Leeward  $C_{p,e}$  from 0 m To 10 m  $C_{p,e} = 0.7$   $p_e = 0.69$  KPa  $p_{net} = 1.02$  KPa

For side wall  $C_{p,e}$  from 0 m To 5.6 m  $C_{p,e} =$   $p_e = -0.64$  KPa  $p_{net} = -0.64$  KPa

Maximum Upward pressure used in roof member Design = 0.89 KPa

Maximum Downward pressure used in roof member Design = 0.43 KPa

Maximum Wall pressure used in Design = 1.02 KPa

Maximum Racking pressure used in Design = 1.18 KPa

**Design Summary**

**Purlin Design**

Purlin Spacing = 900 mm

Purlin Span = 4350 mm

Try Purlin 200x50 SG8 Dry

Moisture Condition = Dry (Moisture in timber is less than 16% and timber does not remain in continuous wet condition after installation)

K1 Short term = 1 K1 Medium term = 0.8 K1 Long term = 0.6 K4 = 1 K5 = 1 K8 Downward = 1.00

K8 Upward = 0.47 S1 Downward = 11.27 S1 Upward = 24.64

Shear Capacity of timber = 3 MPa Bending Capacity of timber = 14 MPa NZS3603 Amt 4, table 2.3

**Capacity Checks**

M <sub>1.35D</sub>	0.72 Kn-m	Capacity	2.23 Kn-m	Passing Percentage	<b>309.72 %</b>
M <sub>1.2D+1.5L 1.2D+S<sub>n</sub> 1.2D+W<sub>nDn</sub></sub>	1.83 Kn-m	Capacity	2.97 Kn-m	Passing Percentage	<b>162.30 %</b>
M <sub>0.9D-W<sub>nUp</sub></sub>	-1.42 Kn-m	Capacity	-1.76 Kn-m	Passing Percentage	<b>123.94 %</b>
V <sub>1.35D</sub>	0.66 Kn	Capacity	9.65 Kn	Passing Percentage	<b>1462.12 %</b>

### Pole Shed App Ver 01 2022

V <sub>1.2D+1.5L 1.2D+Sn 1.2D+WnDn</sub>	1.43 Kn	Capacity	12.86 Kn	Passing Percentage	<b>899.30 %</b>
V <sub>0.9D-WnUp</sub>	-1.30 Kn	Capacity	-16.08 Kn	Passing Percentage	<b>1236.92 %</b>

#### **Deflections**

Modulus of Elasticity = 6700 MPa NZS3603 Amt 4, Table 2.3 considering at least 4 members acting together

k<sub>2</sub> for Long Term Loads = 2

Deflection under Dead and Live Load = 10.76 mm                      Limit by Woolcock et al, 1999 Span/240 = 17.92 mm

Deflection under Dead and Service Wind = 12.83 mm                      Limit by Woolcock et al, 1999 Span/100 = 43.00 mm

#### **Reactions**

Maximum downward = 1.43 kn    Maximum upward = -1.30 kn

Number of Blocking = 0    if 0 then no blocking required, if 1 then one midspan blocking required

#### **Rafter Design Internal**

Internal Rafter Load Width = 4500 mm                      Internal Rafter Span = 9850 mm                      Try Rafter 2x400x63 LVL11

Moisture Condition = Dry (Moisture in timber is less than 16% and timber does not remain in continuous wet condition after installation)

K<sub>1</sub> Short term = 1    K<sub>1</sub> Medium term = 0.8    K<sub>1</sub> Long term = 0.6    K<sub>4</sub> = 1    K<sub>5</sub> = 1    K<sub>8</sub> Downward = 1.00

K<sub>8</sub> Upward = 1.00    S<sub>1</sub> Downward = 6.26    S<sub>1</sub> Upward = 6.26

Shear Capacity of timber = 5 MPa    Bending Capacity of timber = 38 MPa NZS3603 Amt 4, table 2.3

#### **Capacity Checks**

M <sub>1.35D</sub>	18.42 Kn-m	Capacity	58.42 Kn-m	Passing Percentage	<b>317.16 %</b>
M <sub>1.2D+1.5L 1.2D+Sn 1.2D+WnDn</sub>	39.84 Kn-m	Capacity	77.88 Kn-m	Passing Percentage	<b>195.48 %</b>
M <sub>0.9D-WnUp</sub>	-36.29 Kn-m	Capacity	-97.36 Kn-m	Passing Percentage	<b>268.28 %</b>
V <sub>1.35D</sub>	7.48 Kn	Capacity	81.04 Kn	Passing Percentage	<b>1083.42 %</b>
V <sub>1.2D+1.5L 1.2D+Sn 1.2D+WnDn</sub>	16.18 Kn	Capacity	108.06 Kn	Passing Percentage	<b>667.86 %</b>
V <sub>0.9D-WnUp</sub>	-14.74 Kn	Capacity	-135.08 Kn	Passing Percentage	<b>916.42 %</b>

#### **Deflections**

Modulus of Elasticity = 9900 MPa NZS3603 Amt 4, Table 2.3

k<sub>2</sub> for Long Term Loads = 2

Deflection under Dead and Live Load = 23.78 mm                      Limit by Woolcock et al, 1999 Span/240 = 41.67 mm

Deflection under Dead and Service Wind = 31.485 mm                      Limit by Woolcock et al, 1999 Span/100 = 100.00 mm

#### **Reactions**

Maximum downward = 16.18 kn    Maximum upward = -14.74 kn

#### **Rafter to Pole Connection check**

Bolt Size = M12 Number of Bolts = 3

Calculations as per NZS 3603:1993 Amend 2005 clause 4.4

Joint Group for Rafters = J2 Joint Group for Pole = J5

Minimum Bolt edge, end and spacing for Load perpendicular to grains = 60 mm

Factor of Safety = 0.7

For Perpendicular to grain loading

$K_{11} = 12.6$  fpj = 22.7 Mpa for Rafter with effective thickness = 126 mm

For Parallel to grain loading

$K_{11} = 2.0$  fcj = 36.1 Mpa for Pole with effective thickness = 100 mm

Capacity under short term loads = 43.67 Kn > -14.74 Kn

### **Rafter Design External**

External Rafter Load Width = 2250 mm

External Rafter Span = 5531 mm

Try Rafter 300x50 SG8 Dry

Moisture Condition = Dry (Moisture in timber is less than 16% and timber does not remain in continuous wet condition after installation)

$K_1$  Short term = 1     $K_1$  Medium term = 0.8     $K_1$  Long term = 0.6     $K_4 = 1$      $K_5 = 1$      $K_8$  Downward = 0.94

$K_8$  Upward = 0.94     $S_1$  Downward = 13.93     $S_1$  Upward = 13.93

Shear Capacity of timber = 3 MPa    Bending Capacity of timber = 14 MPa NZS3603 Amt 4, table 2.3

### **Capacity Checks**

$M_{1.35D}$	2.90 Kn-m	Capacity	4.72 Kn-m	Passing Percentage	<b>162.76 %</b>
$M_{1.2D+1.5L \ 1.2D+S_n \ 1.2D+W_nD_n}$	6.28 Kn-m	Capacity	6.30 Kn-m	Passing Percentage	<b>100.32 %</b>
$M_{0.9D-W_nUp}$	-5.72 Kn-m	Capacity	-7.87 Kn-m	Passing Percentage	<b>137.59 %</b>
$V_{1.35D}$	2.10 Kn	Capacity	14.47 Kn	Passing Percentage	<b>689.05 %</b>
$V_{1.2D+1.5L \ 1.2D+S_n \ 1.2D+W_nD_n}$	4.54 Kn	Capacity	19.30 Kn	Passing Percentage	<b>425.11 %</b>
$V_{0.9D-W_nUp}$	-4.14 Kn	Capacity	-24.12 Kn	Passing Percentage	<b>582.61 %</b>

### **Deflections**

Modulus of Elasticity = 5400 MPa NZS3603 Amt 4, Table 2.3

$k_2$  for Long Term Loads = 2

Deflection under Dead and Live Load = 9.04 mm

Limit by Woolcock et al, 1999 Span/240 = 20.83 mm

Deflection under Dead and Service Wind = 10.78 mm

Limit by Woolcock et al, 1999 Span/100 = 50.00 mm

### **Reactions**

Maximum downward = 4.54 kn    Maximum upward = -4.14 kn

### **Rafter to Pole Connection check**

Bolt Size = M12 Number of Bolts = 2

Calculations as per NZS 3603:1993 Amend 2005 clause 4.4

Joint Group for Rafters = J5 Joint Group for Pole = J5

Factor of Safety = 0.7

For Perpendicular to grain loading

$K_{11} = 14.9$  fpj = 12.9 Mpa for Rafter with effective thickness = 50 mm

For Parallel to grain loading

$K_{11} = 2.0$   $f_{c,j} = 36.1$  Mpa for Pole with effective thickness = 100 mm

Eccentric Load check

$V = \phi_i \times k_1 \times k_4 \times k_5 \times f_s \times b \times d_s \dots\dots\dots$  (Eq 4.12) = -25.20 kn > -4.14 Kn

Single Shear Capacity under short term loads = -10.84 Kn > -4.14 Kn

### Girt Design Front and Back

Girt's Spacing = 900 mm

Girt's Span = 4500 mm

Try Girt 200x50 SG8 Dry

Moisture Condition = Dry (Moisture in timber is less than 16% and timber does not remain in continuous wet condition after installation)

$K_1$  Short term = 1     $K_4 = 1$      $K_5 = 1$      $K_8$  Downward = 1.00

$K_8$  Upward = 0.78     $S_1$  Downward = 11.27     $S_1$  Upward = 17.82

Shear Capacity of timber = 3 MPa    Bending Capacity of timber = 14 MPa NZS3603 Amt 4, table 2.3

### Capacity Checks

$M_{Wind+Snow}$	2.32 Kn-m	Capacity	2.90 Kn-m	Passing Percentage	<b>125.00 %</b>
$V_{0.9D-WnUp}$	2.07 Kn	Capacity	16.08 Kn	Passing Percentage	<b>776.81 %</b>

### Deflections

Modulus of Elasticity = 6700 MPa NZS3603 Amt 4, Table 2.3

Deflection under Snow and Service Wind = 21.95 mm

Limit by Woolcock et al, 1999 Span/100 = 45.00 mm

Sag during installation = 24.86 mm

### Reactions

Maximum = 2.07 kn

### Girt Design Sides

Girt's Spacing = 1300 mm

Girt's Span = 2500 mm

Try Girt 200x50 SG8 Dry

Moisture Condition = Dry (Moisture in timber is less than 16% and timber does not remain in continuous wet condition after installation)

$K_1$  Short term = 1     $K_4 = 1$      $K_5 = 1$      $K_8$  Downward = 1.00

$K_8$  Upward = 0.73     $S_1$  Downward = 11.27     $S_1$  Upward = 18.79

Shear Capacity of timber = 3 MPa    Bending Capacity of timber = 14 MPa NZS3603 Amt 4, table 2.3

### Capacity Checks

$M_{Wind+Snow}$	1.04 Kn-m	Capacity	2.72 Kn-m	Passing Percentage	<b>261.54 %</b>
$V_{0.9D-WnUp}$	1.66 Kn	Capacity	16.08 Kn	Passing Percentage	<b>968.67 %</b>

### Deflections

Modulus of Elasticity = 6700 MPa NZS3603 Amt 4, Table 2.3

Deflection under Snow and Service Wind = 3.02 mm

Limit by Woolcock et al. 1999 Span/100 = 25.00 mm

Sag during installation = 2.37 mm

#### Reactions

Maximum = 1.66 kn

#### End Pole Design

##### Geometry For End Bay Pole

##### Geometry

275 SED H5 (Minimum 300 dia. at Floor Level)	Dry Use	Height	5300 mm
Area	64885 mm <sup>2</sup>	As	48663.8671875 mm <sup>2</sup>
Ix	335197731 mm <sup>4</sup>	Zx	2331810 mm <sup>3</sup>
Iy	335197731 mm <sup>4</sup>	Zy	2331810 mm <sup>3</sup>
Lateral Restraint	mm c/c		

#### Loads

Total Area over Pole = 11.25 m<sup>2</sup>

Dead	2.81 Kn	Live	2.81 Kn
Wind Down	4.84 Kn	Snow	0.00 Kn
Moment Wind	10.38 Kn-m		
Phi	0.8	K8	0.75
K1 snow	0.8	K1 Dead	0.6
K1 wind	1		

#### Material

Peeling	Steaming	Normal	Dry Use
fb =	36.3 MPa	fs =	2.96 MPa
fc =	18 MPa	fp =	7.2 MPa
ft =	22 MPa	E =	9257 MPa

#### Capacities

PhiNcx Wind	698.09 Kn	PhiMnx Wind	50.59 Kn-m	PhiVnx Wind	115.24 Kn
PhiNcx Dead	418.86 Kn	PhiMnx Dead	30.36 Kn-m	PhiVnx Dead	69.14 Kn

#### Checks

$(M_x/\Phi M_{nx}) + (N/\Phi N_{cx}) = 0.22 < 1$  OK

$(M_x/\Phi M_{nx})^2 + (N/\Phi N_{cx}) = 0.06 < 1$  OK

Deflection at top under service lateral loads = 14.71 mm < 55.86 mm

Ds =	0.6 mm	Pile Diameter
L =	1500 mm	Pile embedment length
f1 =	4200 mm	Distance at which the shear force is applied
f2 =	0 mm	Distance of top soil at rest pressure

#### Loads

Total Area over Pole = 11.25 m<sup>2</sup>

Moment Wind = 10.38 Kn-m  
Shear Wind = 2.47 Kn

#### Pile Properties

Safety Factory 0.55  
Hu = 5.28 Kn Ultimate Lateral Strength of the Pile, Short pile  
Mu = 12.83 Kn-m Ultimate Moment Capacity of Pile

#### Checks

Applied Forces/Capacities = 0.81 < 1 OK

### Drained Lateral Strength of End pile in cohesionless soils Free Head short pile

#### Assumed Soil Properties

Gamma 18 Kn/m<sup>3</sup> Friction angle 30 deg Cohesion 0 Kn/m<sup>3</sup>  
K0 =  $(1 - \sin(30)) / (1 + \sin(30))$   
Kp =  $(1 + \sin(30)) / (1 - \sin(30))$

#### Geometry For End Bay Pole

Ds = 0.6 mm Pile Diameter  
L = 1500 mm Pile embedment length  
f1 = 4200 mm Distance at which the shear force is applied  
f2 = 0 mm Distance of top soil at rest pressure

#### Loads

Moment Wind = 10.38 Kn-m  
Shear Wind = 2.47 Kn

#### Pile Properties

Safety Factory 0.55  
Hu = 5.28 Kn Ultimate Lateral Strength of the Pile, Short pile  
Mu = 12.83 Kn-m Ultimate Moment Capacity of Pile

#### Checks

Applied Forces/Capacities = 0.81 < 1 OK

### Uplift Check

Density of Concrete = 24 Kn/m<sup>3</sup>

Density of Timber Pole = 5 Kn/m<sup>3</sup>

Due to cast in place pile, the surface interaction between soil and pile will be rough thus angle of friction between both is taken equal to soil angle of internal friction

Ks (Lateral Earth Pressure Coefficient) for cast into place concrete piles = 1.5

Formula to calculate Skin Friction = Safety factor (0.55) x Density of Soil(18) x Height of Pile(1800) x Ks(1.5) x 0.5 x tan(30) x Pi x Dia of

Pile(0.6) x Height of Pile(1800)

Skin Friction = 26.17 Kn

Weight of Pile + Pile Skin Friction = 28.89 Kn

Uplift on one Pile = 14.96 Kn

Uplift is ok