First Page

Job No.: 2405021   **Address:** 16 Grant Road Puramahoi,Puramhoi,New Zealand   **Date:** 21/05/2024

Latitude: -40.794148   **Longitude:** 172.738388   **Elevation:** 29 m

General Input

Roof Live Load	0.25 KPa	Roof Dead Load	0.25 KPa	Roof Live Point Load	1.1 Kn
Snow Zone	N2	Ground Snow Load	0 KPa	Roof Snow Load	0 KPa
Earthquake Zone	1	Subsoil Category	D	Exposure Zone	C
Importance Level	1	Ultimate wind & Earthquake ARI	100 Years	Max Height	4.2 m
Wind Region	NZ2	Terrain Category	2.12	Design Wind Speed	37.83 m/s
Wind Pressure	0.86 KPa	Lee Zone	NO	Ultimate Snow ARI	50 Years
Wind Category	High	Earthquake ARI	100		

Note: Wind lateral loads are governing over Earthquake loads, So only wind loads are considered in calculations

Pressure Coefficients and Pressues

Shed Type = Mono   Open

For roof $Cp,i = 0.6475$

For roof CP,e from 0 m To 1.95 m $Cpe = -1.02$ $pe = -0.70$ KPa $pnet = -1.24$ KPa

For roof CP,e from 1.95 m To 3.90 m $Cpe = -0.84$ $pe = -0.58$ KPa $pnet = -1.12$ KPa

For wall Windward $Cp,i = 0.6475$ side Wall $Cp,i = -0.5525$

For wall Windward and Leeward CP,e from 0 m To 18 m $Cpe = 0.7$ $pe = 0.54$ KPa $pnet = 1.05$ KPa

For side wall CP,e from 0 m To 3.90 m $Cpe =$ $pe = -0.50$ KPa $pnet = 0.01$ KPa

Maximum Upward pressure used in roof member Design = 1.24 KPa

Maximum Downward pressure used in roof member Design = 0.66 KPa

Maximum Wall pressure used in Design = 1.05 KPa

Maximum Racking pressure used in Design = 0.93 KPa

Design Summary

Purlin Design

 Purlin Spacing = 900 mm   Purlin Span = 4350 mm   Try Purlin 200x50 SG8 Dry

Moisture Condition = Dry (Moisture in timber is less than 16% and timber does not remain in continuous wet condition after installation)

K1 Short term = 1   K1 Medium term = 0.8   K1 Long term = 0.6   K4 =1   K5 =1   K8 Downward =1.00

K8 Upward =0.80   S1 Downward =11.27   S1 Upward =17.42

Shear Capacity of timber =3 MPa   Bending Capacity of timber =14 MPa NZS3603 Amt 4, table 2.3

Capacity Checks

$M_{1.35D}$	0.72 Kn-m	Capacity	2.23 Kn-m	Passing Percentage	**309.72 %**
$M_{1.2D+1.5L\ 1.2D+Sn\ 1.2D+WnDn}$	2.04 Kn-m	Capacity	2.97 Kn-m	Passing Percentage	**145.59 %**
$M_{0.9D-WnUp}$	-2.16 Kn-m	Capacity	-2.97 Kn-m	Passing Percentage	**137.50 %**
$V_{1.35D}$	0.66 Kn	Capacity	9.65 Kn	Passing Percentage	**1462.12 %**

Second page

$V_{1.2D+1.5L\ 1.2D+Sn\ 1.2D+WnDn}$	1.88 Kn	Capacity	12.86 Kn	Passing Percentage	**684.04 %**
$V_{0.9D-WnUp}$	-1.99 Kn	Capacity	-16.08 Kn	Passing Percentage	**808.04 %**

Deflections

Modulus of Elasticity = 6700 MPa NZS3603 Amt 4, Table 2.3 considering at least 4 members acting together

k2 for Long Term Loads = 2

Deflection under Dead and Live Load = 10.76 mm   Limit by Woolcock et al, 1999 Span/240 = 17.92 mm

Deflection under Dead and Service Wind = 14.89 mm   Limit by Woolcock et al, 1999 Span/100 = 43.00 mm

Reactions

Maximum downward =1.88 kn   Maximum upward = -1.99 kn

Number of Blocking = 1   if 0 then no blocking required, if 1 then one midspan blocking required

Rafter Design Internal

Internal Rafter Load Width = 4500 mm   Internal Rafter Span = 5850 mm   Try Rafter 2x300x50 SG8 Dry

Moisture Condition = Dry (Moisture in timber is less than 16% and timber does not remain in continuous wet condition after installation)

K1 Short term = 1   K1 Medium term = 0.8   K1 Long term = 0.6   K4 =1   K5 =1   K8 Downward =1.00

K8 Upward =1.00   S1 Downward =6.81   S1 Upward =6.81

Shear Capacity of timber =3 MPa   Bending Capacity of timber =14 MPa NZS3603 Amt 4, table 2.3

Capacity Checks

$M_{1.35D}$	3.57 Kn-m	Capacity	10.08 Kn-m	Passing Percentage	**282.35 %**
$M_{1.2D+1.5L\ 1.2D+Sn\ 1.2D+WnDn}$	6.69 Kn-m	Capacity	13.44 Kn-m	Passing Percentage	**200.90 %**
$M_{0.9D-WnUp}$	10.28 Kn-m	Capacity	-16.8 Kn-m	Passing Percentage	**163.42 %**
$V_{1.35D}$	3.85 Kn	Capacity	28.94 Kn	Passing Percentage	**751.69 %**
$V_{1.2D+1.5L\ 1.2D+Sn\ 1.2D+WnDn}$	7.21 Kn	Capacity	38.6 Kn	Passing Percentage	**535.37 %**
$V_{0.9D-WnUp}$	10.83 Kn	Capacity	-48.24 Kn	Passing Percentage	**445.43 %**

Deflections

Modulus of Elasticity = 5400 MPa NZS3603 Amt 4, Table 2.3

k2 for Long Term Loads = 2

Deflection under Dead and Live Load = 9 mm   Limit by Woolcock et al, 1999 Span/240 = 25.00 mm

Deflection under Dead and Service Wind = 24.5 mm   Limit by Woolcock et al, 1999 Span/100 = 60.00 mm

Reactions

Maximum downward =7.21 kn   Maximum upward = 10.83 kn

Rafter to Pole Connection check

Bolt Size = M12 Number of Bolts = 2

Calculations as per NZS 3603:1993 Amend 2005 clause 4.4

Joint Group for Rafters =J5 Joint Group for Pole = J5

Minimum Bolt edge, end and spacing for Load perpendicular to grains = 60 mm

Factor of Safety = 0.7

For Perpendicular to grain loading

K11 = 14.9 fpj = 12.9 Mpa for Rafter with effective thickness = 100 mm

For Parallel to grain loading

K11 = 2.0 fcj = 36.1 Mpa for Pole with effective thickness = 100 mm

Capacity under short term loads = 21.67 Kn > 10.83 Kn

Prop on Sides = 2   2/SG815050Dry   1000mm   Reaction Prop = 13.12 Kn down 20.50 Kn Up

Prop Combined axial and bending ratios (My/Phi x Mny)+(Nc/Phi x Ncy) should be less than or equal to 1

For Short Term Load = 0.99 < 1 OK

For Medium Term Load = 0.79 < 1 OK

For Long Term Load = 0.57 < 1 OK

Prop Connection check

Effective width of Pole used in Calculations = 200 mm -20mm (Margin for chamfer)

Bolt Size = M12 Number of Bolts = 2

Minimum Bolt edge, end and spacing for Load perpendicular to grains = 60 mm

Angle of prop = 45 degree

Prop Connection Capacity under Short term loads: 24.85 Kn > 20.5 Kn OK

Prop Connection Capacity under Medium term loads: 19.88 Kn > 13.12 Kn OK

Prop Connection Capacity under Long term loads: 14.91 Kn > 7.03 Kn OK

Rafter Design External

 External Rafter Load Width = 2250 mm   External Rafter Span = 5830 mm   Try Rafter 300x50 SG8 Dry

Moisture Condition = Dry (Moisture in timber is less than 16% and timber does not remain in continuous wet condition after installation)

K1 Short term = 1   K1 Medium term = 0.8   K1 Long term = 0.6   K4 =1   K5 =1   K8 Downward =0.94

K8 Upward =0.94   S1 Downward =13.93   S1 Upward =13.93

Shear Capacity of timber =3 MPa   Bending Capacity of timber =14 MPa NZS3603 Amt 4, table 2.3

Capacity Checks

$M_{1.35D}$	3.23 Kn-m	Capacity	4.72 Kn-m	Passing Percentage	**146.13 %**
$M_{1.2D+1.5L\ 1.2D+Sn\ 1.2D+WnDn}$	9.18 Kn-m	Capacity	6.30 Kn-m	Passing Percentage	**68.63 %**
$M_{0.9D-WnUp}$	-9.70 Kn-m	Capacity	-7.87 Kn-m	Passing Percentage	**81.13 %**
$V_{1.35D}$	2.21 Kn	Capacity	14.47 Kn	Passing Percentage	**654.75 %**
$V_{1.2D+1.5L\ 1.2D+Sn\ 1.2D+WnDn}$	6.30 Kn	Capacity	19.30 Kn	Passing Percentage	**306.35 %**
$V_{0.9D-WnUp}$	-6.66 Kn	Capacity	-24.12 Kn	Passing Percentage	**362.16 %**

Deflections

4/10

Modulus of Elasticity = 5400 MPa NZS3603 Amt 4, Table 2.3

k2 for Long Term Loads = 2

Deflection under Dead and Live Load = 18.75 mm   Limit by Woolcock et al, 1999 Span/240= 25.00 mm

Deflection under Dead and Service Wind = 25.94 mm   Limit by Woolcock et al, 1999 Span/100 = 60.00 mm

Reactions

Maximum downward =6.30 kn   Maximum upward = -6.66 kn

Rafter to Pole Connection check

Bolt Size = M12 Number of Bolts = 2

Calculations as per NZS 3603:1993 Amend 2005 clause 4.4

Joint Group for Rafters =J5 Joint Group for Pole = J5

Factor of Safety = 0.7

For Perpendicular to grain loading

K11 = 14.9 fpj = 12.9 Mpa for Rafter with effective thickness = 50 mm

For Parallel to grain loading

K11 = 2.0 fcj = 36.1 Mpa for Pole with effective thickness = 100 mm

Eccentric Load check

V = phi x k1 x k4 x k5 x fs x b x ds .... (Eq 4.12) = -25.20 kn > -6.66 Kn

Single Shear Capacity under short term loads = -10.84 Kn > -6.66 Kn

Intermediate Design Sides

Intermediate Spacing = 3000 mm   Intermediate Span = 3750 mm   Try Intermediate 2x200x50 SG8 Dry

Moisture Condition = Dry (Moisture in timber is less than 16% and timber does not remain in continuous wet condition after installation)

K1 Short term = 1   K4 =1   K5 =1   K8 Downward =1.00

K8 Upward =1.00   S1 Downward =11.27   S1 Upward =0.73

Shear Capacity of timber =3 MPa   Bending Capacity of timber =14 MPa NZS3603 Amt 4, table 2.3

Capacity Checks

$M_{Wind+Snow}$	2.77 Kn-m	Capacity	7.46 Kn-m	Passing Percentage	**269.31 %**
$V_{0.9D-WnUp}$	2.95 Kn	Capacity	32.16 Kn	Passing Percentage	**1090.17 %**

Deflections

Modulus of Elasticity = 5400 MPa NZS3603 Amt 4, Table 2.3

Deflection under Snow and Service Wind = 22.52 mm   Limit by Woolcock et al, 1999 Span/100 = 37.50 mm

Reactions

Maximum = 2.95 kn

Girt Design Front and Back

Girt's Spacing = 700 mm   Girt's Span = 4500 mm   Try Girt 150x50 SG8 Dry

Moisture Condition = Dry (Moisture in timber is less than 16% and does not remain in continuous wet condition after installation)

K1 Short term = 1   K4 =1   K5 =1   K8 Downward =1.00

K8 Upward =0.89   S1 Downward =9.63   S1 Upward =15.23

Shear Capacity of timber =3 MPa   Bending Capacity of timber =14 MPa NZS3603 Amt 4, table 2.3

Capacity Checks

$M_{Wind+Snow}$	1.86 Kn-m	Capacity	1.87 Kn-m	Passing Percentage	**100.54 %**
$V_{0.9D-WnUp}$	1.65 Kn	Capacity	12.06 Kn	Passing Percentage	**730.91 %**

Deflections

Modulus of Elasticity = 6700 MPa NZS3603 Amt 4, Table 2.3

Deflection under Snow and Service Wind = 41.65 mm   Limit by Woolcock et al, 1999 Span/100 = 45.00 mm
Sag during installation = 24.86 mm

Reactions

Maximum = 1.65 kn

Girt Design Sides

Girt's Spacing = 1300 mm   Girt's Span = 3000 mm   Try Girt 150x50 SG8 Dry

Moisture Condition = Dry (Moisture in timber is less than 16% and does not remain in continuous wet condition after installation)

K1 Short term = 1   K4 =1   K5 =1   K8 Downward =1.00

K8 Upward =0.79   S1 Downward =9.63   S1 Upward =17.59

Shear Capacity of timber =3 MPa   Bending Capacity of timber =14 MPa NZS3603 Amt 4, table 2.3

Capacity Checks

$M_{Wind+Snow}$	1.54 Kn-m	Capacity	1.65 Kn-m	Passing Percentage	**107.14 %**
$V_{0.9D-WnUp}$	2.05 Kn	Capacity	12.06 Kn	Passing Percentage	**588.29 %**

Deflections

Modulus of Elasticity = 6700 MPa NZS3603 Amt 4, Table 2.3

Deflection under Snow and Service Wind = 15.28 mm   Limit by Woolcock et al. 1999 Span/100 = 30.00 mm
Sag during installation =4.91 mm

Reactions

Maximum = 2.05 kn

Middle Pole Design

Geometry

200 SED H5 (Minimum 225 dia. at Floor Level)		Dry Use	Height	3900 mm
Area		10625 mm2	As	7968.75 mm2
Ix		39982096 mm4	Zx	376302 mm3
Iy		39982096 mm4	Zx	376302 mm3
Lateral Restraint		1300 mm c/c		

Loads

Total Area over Pole = 13.5 m2

Dead	5.45 Kn	Live	4.04 Kn
Wind Down	10.68 Kn	Snow	0.00 Kn
Moment wind	6.63 Kn-m		
Phi	0.8	K8	1.00
K1 snow	0.8	K1 Dead	0.6
K1wind	1		

Material

Peeling		Steaming		Normal		Dry Use	
fb =		36.3 MPa		fs =		2.96 MPa	
fc =		18 MPa		fp =		7.2 MPa	
ft =		22 MPa		E =		9257 MPa	

Capacities

PhiNcx Wind	153.00 Kn	PhiMnx Wind	10.93 Kn-m	PhiVnx Wind	18.87 Kn
PhiNcx Dead	91.80 Kn	PhiMnx Dead	6.56 Kn-m	PhiVnx Dead	11.32 Kn

Checks

$(Mx/PhiMnx)+(N/phiNcx) = 1.06 < 1$ OK

$(Mx/PhiMnx)^2+(N/phiNcx) = 0.98 < 1$ OK

Deflection at top under service lateral loads = 85.86 mm < 39.00 mm

Drained Lateral Strength of Middle pile in cohesionless soils Free Head short pile

Assumed Soil Properties

Gamma	18 Kn/m3	Friction angle	30 deg	Cohesion	0 Kn/m3

$K0 =$ (1-sin(30)) / (1+sin(30))

$Kp =$ (1+sin(30)) / (1-sin(30))

Geometry For Middle Bay Pole

Ds =	0.6 mm	Pile Diameter
L =	1600 mm	Pile embedment length
f1 =	3150 mm	Distance at which the shear force is applied
f2 =	0 mm	Distance of top soil at rest pressure

Loads

Moment Wind =	6.63 Kn-m

Shear Wind =   4.38 Kn

Pile Properties

Safety Factory   0.55

Hu =   7.68 Kn   Ultimate Lateral Strength of the Pile, Short pile

Mu =   14.44 Kn-m   Ultimate Moment Capacity of Pile

Checks

Applied Forces/Capacities = 0.57 < 1 OK

End Pole Design

Geometry For End Bay Pole

Geometry

175 SED H5 (Minimum 200 dia. at Floor Level)   Dry Use   Height   3900 mm

Area   9375 mm2   As   7031.25 mm2

Ix   27465820 mm4   Zx   292969 mm3

Iy   27465820 mm4   Zx   292969 mm3

Lateral Restraint   mm c/c

Loads

Total Area over Pole = 13.5 m2

Dead	3.38 Kn	Live	3.38 Kn
Wind Down	8.91 Kn	Snow	0.00 Kn
Moment Wind	6.90 Kn-m		
Phi	0.8	K8	0.63
K1 snow	0.8	K1 Dead	0.6
K1wind	1		

Material

Peeling	Steaming	Normal	Dry Use
fb =	36.3 MPa	fs =	2.96 MPa
fc =	18 MPa	fp =	7.2 MPa
ft =	22 MPa	E =	9257 MPa

Capacities

PhiNcx Wind	85.24 Kn	PhiMnx Wind	5.37 Kn-m	PhiVnx Wind	16.65 Kn
PhiNcx Dead	51.15 Kn	PhiMnx Dead	3.22 Kn-m	PhiVnx Dead	9.99 Kn

Checks

(Mx/PhiMnx)+(N/phiNcx) = 1.47 < 1 OK

(Mx/PhiMnx)^2+(N/phiNcx) = 1.84 < 1 OK

Deflection at top under service lateral loads = 67.13 mm < 41.90 mm

Ds =   0.6 mm   Pile Diameter

L =   1300 mm   Pile embedment length

f1 =   3150 mm   Distance at which the shear force is applied

f2 =   0 mm   Distance of top soil at rest pressure

Loads

Total Area over Pole = 13.5 m2

Moment Wind =   6.90 Kn-m

Shear Wind =   2.19 Kn

Pile Properties

Safety Factory   0.55

Hu =   4.40 Kn   Ultimate Lateral Strength of the Pile, Short pile

Mu =   8.11 Kn-m   Ultimate Moment Capacity of Pile

Checks

Applied Forces/Capacities = 0.85 < 1 OK

Drained Lateral Strength of End pile in cohesionless soils Free Head short pile

Assumed Soil Properties

Gamma   18 Kn/m3   Friction angle   30 deg   Cohesion   0 Kn/m3

$K_0 =$ (1-sin(30)) / (1+sin(30))

$K_p =$ (1+sin(30)) / (1-sin(30))

Geometry For End Bay Pole

Ds =   0.6 mm   Pile Diameter

L =   1300 mm   Pile embedment length

f1 =   3150 mm   Distance at which the shear force is applied

f2 =   0 mm   Distance of top soil at rest pressure

Loads

Moment Wind =   6.90 Kn-m

Shear Wind =   2.19 Kn

Pile Properties

Safety Factory   0.55

Hu =   4.40 Kn   Ultimate Lateral Strength of the Pile, Short pile

Mu =   8.11 Kn-m   Ultimate Moment Capacity of Pile

Checks

Applied Forces/Capacities = 0.85 < 1 OK

Uplift Check

Density of Concrete = 24 Kn/m3

Density of Timber Pole = 5 Kn/m3

Due to cast in place pile, the surface interaction between soil and pile will be rough thus angle of friction between both is taken equal to soil angle of internal friction

Ks (Lateral Earth Pressure Coefficient)for cast into place concrete piles = 1.5

Formula to calculate Skin Friction = Safecty factor (0.55) x Density of Soil(18) x Height of Pile(1600) x Ks(1.5) x 0.5 x tan(30) x Pi x Dia of Pile(0.6) x Height of Pile(1600)

Skin Friction = 20.68 Kn

Weight of Pile + Pile Skin Friction = 24.83 Kn

Uplift on one Pile = 13.70 Kn

Uplift is ok

Last Page