

BURST STRENGTH TEST REPORT

Shree Packaging Industries

Date: 11-Sep-2026

Sample: 5-ply RSC, BF 22, 180 GSM liner

Mullen burst: 14.2 kg/cm² (spec min 12.0)

Result: PASS