

BURST STRENGTH TEST REPORT

Maruti Cartons

Date: 18-Sep-2026

Sample: 5-ply RSC, BF 22

Mullen burst: 13.1 kg/cm² (spec min 12.0)

Result: PASS