

BYK-065

Silicone defoamer for solvent-borne and solvent-free systems.

Product Data

Composition

Solution of foam-destroying polysiloxanes

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C):	0.95 g/ml
Non-volatile matter (10 min., 150 °C):	0.7 %
Solvents:	Cyclohexanone
Flash point:	43 °C

Special Note

The additive contains fluoro-modified silicone.

Applications

Coatings Industry

Special Features and Benefits

BYK-065 is a defoamer for solvent-borne formulations. It is the more compatible version of BYK-066 N.

Recommended Use

Protective coating systems	■
Architectural coatings	■
Wood and furniture coatings	■

■ particularly recommended

Recommended Levels

0.1-1 % additive (as supplied) based upon total formulation.

The dosage levels are indicated for the purpose of orientation. Optimal dosage levels are determined through series of tests.

Incorporation and Processing Instructions

To achieve optimal defoaming, the defoamer should be added to the millbase. If it is incorporated at a later time, sufficient shear forces must be ensured in order to achieve good defoamer distribution and to prevent crater formation.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany