

Technical Datasheet


TYPE

Methylol type, medium reactive, isobutylated melamine formaldehyde resin

FORM OF DELIVERY (f.o.d.)

55 % in iso-butanol (55IB)

STRUCTURE



PRODUCT DATA

Determined per batch:

Dynamic Viscosity DIN 53177

dynamic viscosity [mPa.s] 220 - 360
(23 °C)

Non-Volatile Matter DIN EN ISO 3251

non-volatile matter [%] 54 - 56
analog
(1 h; 120 °C; 2 g; IB)

Compatibility (aliph. hydrocarbon) DIN EN ISO 11908

dilutability (n-Heptan) [ml/g] 2 - 12
analog
(23 °C)

Not continually determined:

Iodine Colour Number DIN 6162

iodine colour number <1

Density (Liquids) DIN 12791 part 1+3

density [g/ml] 0,99
approx.
(20 °C)

Flash Point (Pensky-Martens) DIN EN 22719

flash point [°C] 33
approx.

Formaldehyde Content (Sulfite) DIN EN ISO 11402


content [%] 2,7
approx.

USES

High overbaking resistance, especially for can coating

FILM PROPERTIES / CLEAR COAT

Maprenal MF 800 (Clear coat: AC/MF = 70/30)



STORAGE

At temperatures up to 25 °C storage stability of Maprenal MF 800/55IB packed in original containers amounts to at least 12 months. Some turbidity may occur in isolated cases but this has no effect on product quality.

Angaben zur Charakterisierung anwendungstechnischer Eigenschaften, wie Verdünnbarkeit, Verträglichkeit sind lediglich als Richtwerte zu betrachten.

01/06

Die in dieser Druckschrift enthaltenen Angaben beruhen auf sorgfältigen Untersuchungen. Sie dienen der Information, befreien den Verwender jedoch nicht von einer eigenverantwortlichen Prüfung für die beabsichtigten Zwecke und Prüfung der Gefahr einer Verletzung etwaiger Schutzrechte Dritter. Die Angaben sind daher unverbindlich und stellen insbesondere keine zugesicherten Eigenschaften im Sinne von Gesetzen dar. Eine Haftung für die Richtigkeit und Vollständigkeit der Angaben ist ausgeschlossen. Es gelten unsere Allgemeinen Geschäftsbedingungen.

	World Area		Customer Order	Technical Support
INEOS Melamines, Inc. 1950 Lake Park Drive Smyrna, GA 30080 U.S.A.	North America	TEL	+1 888 723 2873	+1 413 730 2757
		L	+1 777 970 8940	+1 413 730 3444
INEOS Melamines GmbH Alt Fechenheim 34 D 60386 Frankfurt, Germany www.ineosmelamines.com	South America	TEL	+1 888 723 2873	+1 413 730 2757
		L	+1 777 970 8940	+1 413 730 3444
	Europe-Africa	TEL	+49 (0) 69 4109 2319	+49 (0) 69 4109 2310
		L	+49 (0) 69 4109 2552	+49 (0) 69 4109 2628
	Asia Pacific	TEL	+49 (0) 69 4109 2319	+49 (0) 69 4109 2310
		L	+49 (0) 69 4109 2552	+49 (0) 69 4109 2628

NOTICE: Although the information and recommendations set forth herein (hereinafter "Information") are presented in good faith and believed to be correct as of the date hereof, Ineos Melamines Inc. (and its subsidiaries) makes no representations or warranties as to the completeness or accuracy thereof. Information is supplied upon the condition that the persons receiving same will make their own determination as to the suitability for their purpose prior to use. In no event will Ineos Melamines Inc. be responsible for damages of any nature whatsoever resulting from the use of or reliance upon Information or the product to which Information refers. Nothing contained herein is to be construed as a recommendation to use any product, process, equipment or formulation in conflict with any patent, and Ineos Melamines Inc. makes no representation or warranty, express or implied, that the use thereof will not infringe any patent. Certain products may not be regulated or available in some world areas. NO REPRESENTATIONS OR WARRANTIES, EITHER EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR OF ANY OTHER NATURE ARE MADE HEREUNDER WITH RESPECT TO INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS. Where indicated, ® is a Registered Trademark of Ineos Melamines Inc.