

OXYESTER T 1136

GENERAL DESCRIPTION

Oxyester T 1136 is a saturated polyester diol. It is supplied as a solvent-free, clear liquid of medium viscosity.

SPECIFICATION

| Property | Value | Unit | Test method |
|--------------------|-----------|----------|-------------------------|
| Hydroxyl number | 107 ± 10 | mg KOH/g | DIN 53 240 / ASTM E 222 |
| Viscosity at 23 °C | 4.0 ± 0.8 | Pa·s | DIN EN ISO 3219 |

TYPICAL DATA

| Property | Value | Unit | Test method |
|--------------------------|-------------|-------------------|--------------------------|
| Hydroxyl content | approx. 3.2 | % by wt. | - |
| Acid number | < 2 | mg/KOH/g | DIN EN ISO 3682 |
| Water content | < 0.1 | % by wt. | DIN 51 777 |
| Density at 25 °C | 1.09 | g/cm ³ | DIN 51 757 / ASTM D 2111 |
| Setting point | - 23 | °C | DIN 51 583 |
| Flash point (open cup) | 231 | °C | DIN 51 584 |
| Flash point (closed cup) | 160 | °C | DIN 51 758 |
| Colour (APHA) | ≤ 150 | | DIN/ISO 6271 |
| Ignition temperature | 430 | °C | DIN 51 794 |

PROPERTIES AND APPLICATIONS

Oxyester T 1136 is a linear polyester diol characterized by its good compatibility with commercially available PUR resins. It has been developed primarily for the use in aliphatic PUR technology. The main application is as a flexibilizing polyol, e.g. in combination with trifunctional polycaprolactones like Capa® 305 (Interlox) or Tone® 305 (Union Carbide) for PUR elastomers, as well as in 2K PUR high-solids paints or 1K stoving systems. Oxyester T 1136 is also a suitable polyol for the production of air-drying PUR resins (waterborne polyurethane dispersions or solventborne systems).

COMPATIBILITY AND SOLUBILITY

Oxyester T 1136 is compatible with many resins and additives used in the production of polyurethane compounds. The solubility of this polyester in ketones, esters and aromatics is an important requirement for paint applications.

STORAGE AND PACKAGING

Oxyester T 1136 can be stored in unopened containers for at least one year without loss of quality in accordance with the above specification.

At storage temperatures < 5 °C turbidity may occur. This can be reversed by warming up to 30 – 40 °C.

It is supplied in 25 kg cans and 200 kg non returnable drums.

SAFETY AND HANDLING

Please refer to our Material Safety Data Sheet.

Marl, June 10, 2018; This data sheet replaces all former issues.

VESTANAT® is a registered trademark of Evonik Industrie AG or one of its subsidiaries.

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

For contact in your country, please visit: www.evonik.com/crosslinkers-contact

EVONIK CORPORATION

Business Line Crosslinkers
299 Jefferson Road,
Parsippany, NJ 07054-0677
USA

EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers
55, Chundong Road
Xinzhuang Industry Park
Shanghai, 201108
China

