GUJARAT PRINT PACK PUBLI

F-QC-14/00

INTERNAL TEST RELIABILIT

Paper Reel SAP batch no.	GSM - Total Specification : 70 ± 5%			
	Inspector - 1 (Kapila)	Inspector - 2 (Kirti Patel)	Inspector - 3 (Anil Raval)	Inspector - 4 (Karan Prajapati)
9460/5234/15	72	71	70	71
9460/5234/14	70	71	72	71
9460/5234/16	71	72	72	71
Conclusion	Variation are within specification limit, hence test reliability accepted			

Roll no.	GSM - Adhesive Specification : 16.0 ± 2			
	Inspector - 1 (Kapila)	Inspector - 2 (Kirti Patel)	Inspector - 3 (Anil Raval)	Inspector - 4 (Karan Prajapati)
9460/5234/15	14	15	15	15
9460/5234/14	15	14	16	14
9460/5234/16	15	15	14	15
Conclusion	Variation are within specification limit, hence test reliability accepted			

Roll no.	Thickness Specs : 110 micron			
	Inspector - 1 (Kapila)	Inspector - 2 (Kirti Patel)	Inspector - 3 (Anil Raval)	Inspector - 4 (Karan Prajapati)
9460/5234/15	110	110	110	110
9460/5234/14	110	110	110	110
9460/5234/16	110	110	110	110
Conclusion	Variation are within specification limit, hence test reliability accepted			

Roll no.	Peel Strength Specs : More than 1000 gms			
	Inspector - 1 (Kapila)	Inspector - 2 (Kirti Patel)	Inspector - 3 (Anil Raval)	Inspector - 4 (Karan Prajapati)
9460/5234/15	1176	1220	1160	1190
9460/5234/14	1147	1178	1192	1184
9460/5234/16	1190	1185	1187	1177
Conclusion	Variation are within specification limit, hence test reliability accepted			