GUJARAT PRINT PACK PUBI

INTERNAL TEST RELIABILITY RI

Roll no.	Thickness: 40 micron			
	Inspector - 1 (Kapila)	Inspector - 2 (Kirti Patel)	Inspector - 3 (Anil Raval)	Inspector - 4 (Karan Prajapati)
9460/5234/15	40	40	40	40
9460/5234/14	40	40	40	40
9460/5234/16	40	40	40	40
Conclusion	Variation are within specification limit, hence test reliability accepted			

Roll no.	Shrinkage Ratio : TD 60 ± 2 %, MD 0 ~ 6%			
	Inspector - 1 (Kapila)	Inspector - 2 (Kirti Patel)	Inspector - 3 (Anil Raval)	Inspector - 4 (Karan Prajapati)
9396/5146/1	TD-61 MD-3	TD-60,MD-3	TD-62,MD-3	TD-61,MD-3
9396/5146/5	TD60,MD-4	TD60,MD-4	TD61,MD-4	TD60,MD-4
9396/5146/8	TD-61,MD-3	TD-61,MD-3	TD-60,MD-3	TD-62,MD-3
Conclusion	Variation are within specification limit, hence test reliability accepted			

Roll no.	Corona Treatment - Both side Min. 36 dynes			
	Inspector - 1 (Kapila)	Inspector - 2 (Kirti Patel)	Inspector - 3 (Anil Raval)	Inspector - 4 (Karan Prajapati)
9396/5146/1	Pass	Pass	Pass	Pass
9396/5146/5	Pass	Pass	Pass	Pass
9396/5146/8	Pass	Pass	Pass	Pass
Conclusion	Variation are within specification limit, hence test reliability accepted			