GUJARAT PRINT PACK PUBLICATIONS PVT LTD

ADHESIVE MIXING RATIO RECORD

FORMAT NO.	REV NO.	DATE	PAGE NO.
F-QC-32	00	10-Oct-2026	1 of 1 (digital)

One row per adhesive batch mixed. Standard mix observed on the specimen: 15 kg adhesive : 1.65 kg hardener : 19.5 kg ethyl acetate.

SR. NO.	TIME	ADHESIVE (KG)	HARDENER (KG)	ETHYL (KG)	VISCOSITY (SEC.)	REMARK	CHECKED BY	VERIFIED BY
1	10:04	15	1.65	19.5	19.89		Jeni	
2	13:25	15	1.65	19.5	19.8		Jeni	
3	21:04	15	1.65	19.5	20.18		Singh	