

Important notice: Powermax products must be tested by the user for compliance with the equipment and production treatment applied by the user. Powermax is not liable for any injury, direct or consequential, arising from the use of, or inability to use Powermax products. The maximum obligation of Powermax is to replace any product supplied by Powermax, which has been proven to be defective.

Technical Data: TEXIMAX CP-e 125 S

TEXIMAX CP-e 125 S is the highest quality transfer paper for Screen printing on textile with water based inks.

TEXIMAX CP-e 125 S is designed for cold peel transfers.
Basic weight of the paper is 125g./sm.

Screen printing:

Printing side is the side with thicker silicone coating and is much easier for peeling.

We recommend opening the packaging and cutting on final printing size one day earlier before printing in reason to optimize the stability of the paper.

Storage: **Teximax CP-e 125S** must be stored at room temperature and dry environment with no exposure to moisture.

Pre-conditioning for screen printing: **TEXIMAX CP-e 125S** is necessary pre-heating, before screen printing, through drier on recommended temperature 140°C-150°C for 45 seconds.

Recommended processing-time: within one year from the date of production.

Final appearance after transferring on textil -GLOSSY.

Transfer process:

Application temperatures: 180° to 200°C

Dwell time 10–15 seconds

Pressure: Medium (35 to 45 psi)

Packaging: 200 Sheets 100 x 70 cm

400 Sheets 50 x 70 cm

Other sizes are available on customer request.

Producer: Powermax d.o.o. Backa Palanka
Vuka Karadzica str. 15
21400 Backa Palanka
Serbia

Tel. +38121753533; +38121754066
Mob.+381603377946

