

**AMENDMENT NO. 2 MARCH 2010
TO
IS 15652 : 2006 INSULATING MATS FOR ELECTRICAL
PURPOSES — SPECIFICATION**

(Page 1, clause 1.1, last line) — Substitute ‘33’ for ‘66’.

(Page 1, clause 4.1, first line) — Substitute ‘Three’ for ‘Four’.

[Page 1, Table 1, Sl No. (iv)] — Delete the entire row.

(Page 1, clause 4.2, first sentence) — Substitute ‘acid/alkali and oil and low temperature’ for ‘acid and oil and low temperature’.

(Page 1, clause 4.2) — Add the following new para at the end:

‘Mats resistant to acid and oil and low temperature (Category I) and mats resistant to alkali and oil and low temperature (Category II) shall be considered to be different product groups. Thus, mats resistant to acids, alkali & oil and low temperature (Category III) shall be considered to be conforming to both the product groups.’

(Page 2, clause 6.3) — Add the following new subclause at the end:

‘**6.3.1** Mats of higher thickness than those specified in the Table 2 inclusive of tolerances are permissible subject to their passing the specified tests. Manufacturers of such mats shall declare that thickness and the tolerances of ± 10 percent shall be applicable on the declared thickness.’

[Page 2, Table 2, Sl No. (iv)] — Delete the entire row.

[Page 3, Table 4, Sl No. (iv)] — Delete the entire row.

[Page 3, Table 5, Sl No. (iv)] — Delete the entire row.

[Page 3, clause 9.1(a)] — Substitute the following for the existing:

‘a) Class, Category and thickness,’

(Page 5, Annex C, clause C-2, first sentence) — Substitute the following for the existing:

‘Five dumb-bell test pieces shall be prepared in accordance with IS 10810 (Part 7).’

Amend No. 2 to IS 15652 : 2006

(Page 6, Annex C, clause C-3.4, second para) — Substitute the following for the existing:

‘The matting or test piece shall be placed over the mask. A rectangular metal plate, 762 mm × 762 mm and approximately 5 mm thick, having smoothly rounded edges and corners, shall be placed on top of the matting or test piece. This top plate shall then be energized with the test voltage.’

(Page 6, Annex C, clause C-4) — Substitute the following for the existing:

‘Subsequent to subjecting the mat to ageing as described in 8.3, the tensile strength and elongation at break shall be measured as described in C-2.’

[Page 7, Annex C, clause C-6 (see also Amendment No.1)] — Substitute the following for the existing:

‘C-6 EFFECTS OF ACID/ALKALIS AND OIL

The test pieces shall be conditioned by immersion in each of the desired medium, namely, 30 percent concentrated sulphuric acid, 30 percent concentrated NaOH LR Grade, HSD and Transformer Oil conforming to IS 335, as per product classification in line with 4.2, for 48 h at room temperature. After conditioning in the given agent, the test pieces shall be dried for 4 h at room temperature before subjecting to test. Tensile strength and elongation at break shall be measured as described in C-2.’

(Page 9, Annex E, Table 7, col 1, row 7) — Substitute the following for the existing:

‘Acid/alkali & oil resistance’

(ET 02)