

AMENDMENT NO. 2 APRIL 2013
TO
IS 15766 (Part 2) : 2007 GRADING OF POLISHED DIAMONDS
PART 2 TEST METHODS

(Page 40, clause 10.1) — Insert the following at the end:
‘Some examples of symmetry deviation are also given in Fig. 99.’




Girdle outline not circular		Crown facets not pointing up	
Slanting table		Varying girdle thickness	
Sloping (illustrated) or wavy girdle		Alternating girdle Thickness	
Culet out of centre		Crown side not aligned to pavilion side	
Table out of centre		Cone-shaped girdle	
Table and culet out of centre either in the opposite (illustrated) or same direction		Girdle partly faced	
Table and/or star facets not symmetrical		Pavilion facets not symmetrical	
Bezels not symmetrical		Lower girdle facets not symmetrical	
Upper facets not symmetrical		Pavilion facets not pointing up	

Figure 99 Examples of symmetry deviations

(Page 40, clause 10.1) — Insert the following new clauses after 10.1:

‘10.2 Polish

When determining the optional polish grade, the characteristics listed in B-3 of IS 15766 (Part 1) shall be taken into account. The diamond shall be graded in accordance with Table 8.

Price Group 2

Amendment No. 2 to IS 15766 (Part 2) : 2007

A combination of 10 X magnification and naked eye observations shall be used to assign the categories listed in Table 8.

Table 8 – Polish Characteristics

Visibility 10 X (1)	Optional Polish Grade			Polish Grade Not Given	
	Option 1 (2)	Option 2 (3)	FL or IF – LC (4)	Comments to be made (5)	FL or IF –LC (6)
Not found or very hard to find	Very good	Ex	FL - LC		FL - LC
Hard to find		Very good	IF - LC	Negligible external characteristic ¹⁾	IF - LC
Fairly hard to find	Good	Good	IF - LC	External characteristic ¹⁾	IF - L C
Easy to find	Fair/Medium, specified description	Fair/Medium, specified description	IF - LC	Specified description	IF - LC
Very easy to find easily visible to the naked eye	Poor, specified description	Poor, specified description	IF - LC	Specified description	IF - LC
¹⁾ Description only to be mentioned with LC and IF, specified description for example 'important burn mark'. 'Important polishing lines'; the most important description alone shall be mentiond.					

11 EXPRESSION OF RESULTS

Results or grades shall be expressed in a test report in accordance with the manner and wording indicated in all parts of IS 15766.

12 COMMENTS

The sections in a test report that are reserved for the insertion of additional comments shall be used, for example for,

- structural phenomena (growth characteristics) (see Table 3 and Table 4);
- proportions comments (see Table 5); and
- external characteristics (see Table 9).

Table 9 — External Characteristics (Naturals and Extra Facts)

SI No.	Naturals and extra facets visible with 10 x loupe	Comments
(1)	(2)	(3)
i)	Very small and located on the pavilion	No mention
ii)	Small and located on the pavilion or girdle; not visible from the crown side	Optional mention
iii)	Visible from the crown side	Small external characteristics
iv)	Clearly visible from the crown	Specified description
NOTE — Also related to symmetry categories (see 10.1 and Tables 6 and Table 7).		

13 TEST REPORT

The test report shall contain at least the following information:

- Reference to this standard;
- Results of the following tests:
 - clarity;
 - colour;
- Comments (if applicable);
- Long-wave ultraviolet fluorescence;

Amendment No. 2 to IS 15766 (Part 2) : 2007

- e) Measurements;
- f) Plot of internal characteristics/inclusions and external characteristics/blemishes;
- g) Proportions (table size, crown height and or crown angle, pavilion depth and or pavilion angle, girdle thickness, culet size);
- h) Reference code;
- j) Shape and cut;
- k) Symmetry;
- m) Weight; and
- n) Date of the test.