

AMENDMENT NO. 1 MARCH 2018
TO
IS 15779 : 2007 METAL COMPLEX SYNTANS —
SPECIFICATION

(*Page 1, Table 1*) — Substitute the following *for* the existing table:

Table 1 Requirement for Metal Complex Syntans
(*Clause 5*)

Sl No.	Characteristic	Requirement	Method of Test, Ref to
(1)	(2)	(3)	(4)
i)	Moisture content, percent by mass, <i>Max</i>	7.0	7 of IS 13271
ii)	Total metal oxides, percent by mass, <i>Min</i>	10.0	Annex A
iii)	Total ash content, percent by mass, <i>Max</i>	35.0	16 of IS 13271
iv)	pH of 10 percent solution, <i>Min</i>	2.5	13 of IS 13271
v)	Total free formaldehyde, ppm, <i>Max</i>	50.0	CHD 17 (10756)F ¹⁾

¹⁾ Document under printing.