

AMENDMENT NO. 1 NOVEMBER 2020

TO

IS 15827 : 2019 CLADDING FILMS FOR GREENHOUSE/ POLYHOUSE — SPECIFICATIONS

(*First Revision*)

(Page 3, Table 1) — Substitute the following for existing table:

Table 1 Type of Cladding Films Based on Properties Required

(*Clause 4.1*)

Sl No.	Type of Film	Properties
(1)	(2)	(3)
i)	A - Clear Film	Diffusion – <i>Max</i> 30 percent
ii)	B - 30 percent Diffused Film	Diffusion – <i>Min</i> 30 percent and <i>Max</i> 50 percent
iii)	C - 50 percent Diffused Film	Diffusion – <i>Min</i> 50 percent and <i>Max</i> 70 percent
iv)	D - 50 percent Diffused Film	Diffusion – <i>Min</i> 50 percent and <i>Max</i> 70 percent, Anti-Sulphur, UV Blocking
v)	E - 70 percent Diffused Film	Diffusion – <i>Min</i> 70 percent
vi)	F - 70 percent Diffused Film	Diffusion – <i>Min</i> 70 percent, Anti-Sulphur, UV Blocking

NOTE — All the films shall be UV stabilized and with anti dust, anti drip/anti-fog/anti-mist and ir thermic, properties.

Price Group 1

(Page 4, Table 2) — Substitute the following for existing table:

Table 2 Recommended Technical Data Sheet for Type of Cladding Films as Given in Table 1

(Clauses 6.3 and 7.5.5)

Sl No.	Characteristics	Recommended Values						
		(3)	(4)	(5)	(6)	(7)	(8)	(9)
(1)	(2)	A	B	C	D	E	F	
i)	Tensile strength at Break (MD) MPa (<i>Min</i>)	20	20	20	20	20	20	IS 13360 (Part 5/Sec 3)
ii)	Tensile strength at Break (TD) MPa (<i>Min</i>)	20	20	20	20	20	20	IS 13360 (Part 5/Sec 3)
iii)	Elongation at Break (MD) (<i>Min</i>)	700	700	700	700	700	700	IS 13360 (Part 5/Sec 3)
iv)	Elongation at Break (TD) (<i>Min</i>)	700	700	700	700	700	700	IS 13360 (Part 5/Sec 3)
v)	Dart drop test on flat sheet, Method B gm (<i>Min</i>)	450	450	450	450	450	450	IS 13360 (Part 5/Sec 6)
vi)	Total visible light transmittance (<i>Min</i>) percent	85	85	85	85	85	85	IS 13360 (Part 9/Sec 5)
vii)	Haze, percent	≤30	30-50	50-70	50-70	>70	>70	IS 13360 (Part 9/Sec 5)
viii)	Tear strength, N/mmm (<i>Min</i>)							
	MD	8	8	8	8	8	8	IS 13360 (Part 5/Sec 10)
	TD	12	12	12	12	12	12	IS 13360 (Part 5/Sec 10)
ix)	Thermicity IR Effectiveness (<i>Min</i>), percent	50	55	60	65	65	70	See 7.4
x)	Creep test MD, percent (<i>Max</i>)	30	30	30	30	30	30	See 7.3

(Page 4, *clause 7.2.4*) — Insert the following at the end:

NOTE — Tolerance on the width of film may be allowed as per the mutual agreement between the purchaser and the manufacturer.