

AMENDMENT NO. 1 MAY 2019
TO
IS 15844 : 2010 SPORTS FOOTWEAR — SPECIFICATION

(Page 2, clause 3.4) — Insert the following new clause and renumber the subsequent clauses and tables accordingly:

3.5 Lining

The vamp lining and quarter lining used in the sports footwear shall conform to various requirements as given in Table 6. The use of quarter lining in sports footwear is optional.

Table 6 Requirements for Vamp and Quarter Lining
(Clause 3.5)

Sl No.	Characteristic	Requirement	Method of Test, Ref to
(1)	(2)	(3)	(4)
i)	Tear strength, N, <i>Min</i> :		See 6.3 of IS 15298 (Part 1) ¹⁾
	a) Leather	30	
	b) Coated fabric and textile	15	
ii)	Abrasion resistance, No. of cycles, <i>Min</i> :		See 6.12 of IS 15298 (Part 1) ¹⁾
	a) Dry – 25 600	No holes	
	b) Wet – 12 800	No holes	
iii)	Water vapour permeability, mg/(cm ² .h), <i>Min</i> :	2.0	See 6.6 of IS 15298 (Part 1) ¹⁾
iv)	Water vapour coefficient, mg/cm ² , <i>Min</i>	20	See 6.8 of IS 15298 (Part 1) ¹⁾
v)	pH value (for leather lining), <i>Min</i>	3.2	See 6.9 of IS 15298 (Part 1) ¹⁾
vi)	Chromium VI content (for leather lining), mg/kg, <i>Max</i>	3.0	IS 16259

¹⁾ IS 15298 (Part 1) : 2015

Amendment No. 1 to IS 15844 : 2010

(Page 7, Table 15) — Substitute the following for the existing table:

Table 15 Counter Material: Thermoplastic, Solvent Activated and Heat Activated Sheets
(Clause 3.10)

Sl. No	Characteristics	Requirements			Methods of Test, Ref to
		Casuals	Medium Performance	High Performance	
(1)	(2)	(3)	(4)	(5)	(6)
i)	First dry collapsing load, hardness, N, <i>Min</i>	< 30	130 – 31	> 130	See A-3.2.6 of IS 7554
ii)	Resilience, percent, <i>Min</i> :				See A-3.4 of IS 7554
	a) All types other than filmic material	50	35	25	
	b) For filmic materials	70	45	30	
iii)	Moisture resistance, percent, <i>Min</i>	40	60	80	See A-3.5 of IS 7554
iv) a)	Initial dry area shape retention, percent, <i>Min</i>	55	70	85	See A-3.1 of IS 7554
b)	Area shape retention after 10 th collapse, dry, percent, <i>Min</i>	45	60	75	See A-3.3 of IS 7554
v)	Peel strength, N/cm, <i>Min</i>	5	5	5	See Annex B of IS 7554

(Page 7, Annex A) — Insert the following new entries at appropriate places :

<i>IS No.</i>	<i>Title</i>
7554 : 2009	Toe puff and counter stiffener — Specification (<i>first revision</i>)
15298 (Part 1) : 2015	Personal Protective Equipment Part 1 Test Methods for Footwear (<i>second revision</i>)
16259 : 2014	Leather Chemical Tests Determination of Chromium VI Content' <i>after</i> IS 15298 (Part 1) : 2002.

(CHD 19)

Publication Unit, BIS, New Delhi, India