

**AMENDMENT NO. 1 MAY 2002
TO
IS 12436 : 1988 SPECIFICATION FOR PREFORMED RIGID
POLYURETHANE (PUR) AND POLYISOCYANURATE (PIR)
FOAMS FOR THERMAL INSULATION**

[Page 2, Table 1, Sl No. (i), col 7] — Substitute 'Part 3' for 'Part 2'.

[Page 2, Table 1, Sl No. (v)] — Substitute the following for the existing text:

(1)	(2)	(3)	(4)	(5)	(6)	(7)
'v)	Thermal conductivity (W/m.k), Max, (see Appendix A), at:					
	50°C	0.03	0.03	0.03	0.03	} IS 3346 : 1980†
	10°C	0.023	0.023	0.023	0.023	

(Page 3, clause A-1.1, line 1) — Substitute 'IS 14164 : 1994*' for 'IS 7240 - 1981* and IS 7413 - 1981†'.

(Page 3, footnotes) — Substitute the following for the existing footnotes:

Industrial application and finishings of thermal insulation materials at temperatures above –80°C and up to 750oC – Code of practice.

(Page 3, clause A-3.1.1) — Delete.

(CHD 27)