Free amendment provided by BIS via BSB Edge Private Limited to Flushing(prajwalkoirala638@gmail.com)
113.199.238.108

AMENDMENT NO. 1 SEPTEMBER 1995
TO
IS 12550 : 1988 METHODS FOR DETERMINING PARTICLE SIZE DISTRIBUTION OF IRON ORE FINES

(*Page* 4, *clause* 6.4.9.1, *line* 7) — Substitute '$\frac{W_L}{W_B} \times 100$' *for* '$\frac{W_L}{W_B}$'.

(*Page* 5, *Annex* A) — Substitute the following for the existing Annex:

"**ANNEX A**

(*Clause* 6.3.4, *Note* 1)

AN EXAMPLE OF THE METHOD OF DETERMINATION OF SIZE DISTRIBUTION OF A SUB-LOT SAMPLE OF FINES, BY SIEVING AND CALCULATION OF SIZE DISTRIBUTION ON AS-RECEIVED BASIS

SUB-LOT SAMPLE FOR SIZE DISTRIBUTION (approximately 17 kg)

↓

SIEVING	Mass (kg)	Mass (percent)	Final Mass (percent) (On as-received basis)
+ 10 mm	NIL	—	—
↓			
— 10/+ 4·75 mm	1·140	6·71	6 83
↓			
— 4·75 mm	15·860	93·29	—

↓

MIXING AND DIVISION

↓ SAMPLE (1·79 kg) ↓ REJECT

↓

DRYING

↓

SIEVING

	MASS (g)	MASS (%)	MASS PERCENT CALCULATED ON AS-RECEIVED BASIS (Split into further size fraction) Mass (%) × 93·29 / 100
+ 2·6 mm	140	7·82	7·29
↓			
— 2·6/+ 1·7 mm	300	16·76	15·64
↓			
— 1·7/+ 0·5 mm	370	20·67	19·28
↓			
— 500/+ 150 μm	830	46·37	43·26
↓			
— 150 μm	150	8·38	7·82
		100·00	Total 93·29

NOTE — '+' sign prefixed to a sieve aperture size indicates material retained on that sieve after sieving; '—' sign indicates material passing through that sieve after sieving."

Printed at New India Printing Press, Khurja, India