

**AMENDMENT NO. 1 JANUARY 1993
TO
IS 12583 : 1988 SPECIFICATION FOR CORRUGATED
BITUMEN ROOFING SHEETS**

(Page 1, clause 3.1) — Insert the following size at the end:

<i>Length</i> (mm)	<i>Width</i> (mm)	<i>Thickness</i> (mm)	<i>Depth of Corrugation</i> (mm)	<i>Pitch of Corrugation</i> (mm)
1 800	900	3 to 5	35	90'

(Page 1, clause 3.2, Note) — Insert the following at the end:

'The tolerance in thickness shall be +1 mm.'
0

[Page 1, Table 1, Sl No. (i), col 3] — Substitute '3 to 5' for '5'.

(Page 2, Table 2) — Insert the following matter at the end:

<i>SL No.</i> (1)	<i>SIZE</i> (2) mm	<i>THICKNESS</i> (3) mm	<i>MASS</i> (4) kg
ii)	1 800 × 900	3	5.4 ± 0.2
		4	7.2 ± 0.2
		5	9.0 ± 0.2'

(Page 2, clause 6.1, last sentence) — Substitute the following for the existing sentence:

'External surface of the sheets shall be painted.'

(Page 2, Table 3, Sl No. (i), col 3] — Delete the words 'Not to exceed'.

(CED 5)

Reprography Unit, BIS, New Delhi, India