

AMENDMENT NO. 1 OCTOBER 1996
TO
IS 12630 : 1989 PYROTECHNICS — FIREWORKS
BLACK SERPENT PELLETS — SPECIFICATION

(Page 1, clause 4) — Substitute '**SIZES**' for '**GRADES**'.

(Page 1, clause 4.1, line 2) — Substitute 'sizes' for 'grades'.

(Page 1, Table 1, col 2, title) — Substitute 'Size' for 'Grade'.

(Page 1, clause 5.1, last sentence) — Insert 'any appreciable' between the words 'produce' and 'flame'.

(Page 1, clause 5.1.5) — Substitute the following for the existing text:

'The construction, composition and mass of the pyrotechnic charge shall be as approved by the Chief Controller of Explosives. The pyrotechnic composition may contain one or more of the following chemicals:

- a) Nitrated pitch,
- b) Barium nitrate (see IS 4396 : 1981),
- c) Red phosphorus (see IS 2012 : 1961),
- d) Nitro cellulose,
- e) Calcium carbonate (see IS 7633 : 1982), and
- 1) Dextrin (see IS 12276 : 1988) or gum.'

(Page 2, clause 6.1, second sentence) — Substitute the following for the existing sentence:

'The fireworks black serpent pellets of both the sizes shall be packed in boxes of five pieces.'

[Page 2, clause 6.2.1(a) and (b)]:

Delete the word 'type' and substitute 'size' for 'grade'.

Substitute 'Indication of the source of manufacture ;' for 'Name of the manufacturer and/or his recognized trade-mark, if any;'

Amend No. 1 to IS 12630 : 1989

(Page 2, clause C-2.1) — Substitute the following for the existing text:

'Take 5.0 g of the sample Pyrotechnic composition in a 250-ml beaker. Add 50 ml of water and stir well. Digest for 2 minutes by slight warming. Allow it to cool and then filter. To the Citrate add 50 ml of aniline hydrochloride reagent. The material shall be considered chlorate free if there is no bluish green precipitation or colouration.'

(Page 3, Annex E) — Substitute the following for the existing text:

E-1 GENERAL

E-1.1 The test is carried out by placing the fireworks black serpent pellets in an oven maintained at 100°C and examining them after 2 h for ignition.

E-2 APPARATUS

E-2.1 Air Oven

It shall be fitted with a thermometer graduated up to 150°C and shall not have an exposed heating coil.

E-3 PROCEDURE

E-3.1 Take six pieces of fireworks black serpent pellets and place them on watch glasses inside an air oven. Close the door of the oven and raise the temperature to 100°C. Maintain the assembly under this condition for 2 h.

E-3.2 The samples shall be taken to have passed the test if the fireworks black serpent pellets do not ignite during the test.'

(Page 3, clause F-1.1) — Substitute the following for the existing text:

F-1.1 Place five pieces of fireworks black serpent pellets on separate watch glasses and ignite them. Ensure that the whole mass of the pellets burns completely and continuously. Do not disturb the bodies of ash formed on ignition of the pellets. Measure the lengths of the bodies of black ash from each of the five pellets by placing threads along their lengths and subsequently measuring the lengths of the threads with a scale.'

(CHD 026)

Reprography Unit, BIS, New Delhi, India