

AMENDMENT NO. 1 OCTOBER 1995
TO
IS 12709 : 1994 GLASS FIBRE REINFORCED PLASTICS
(GRP) PIPES, JOINTS AND FITTINGS FOR USE FOR
POTABLE WATER SUPPLY — SPECIFICATION
(First Revision)

(Page 3, Table 2) — Add the following at the end:

Nominal Diameter, DN	Outside Diameter, OD	Tolerance	
2 200	2 248	+7.0	
2 400	2 452	+7.5	
2 600	2 656	+8.0	-2.0
2 800	2 860	+8.5	
3 000	3 064	+9.0	

(Page 11, Annex E, clause E-6.1) — Substitute the following for the existing:

"E-6.1 For each test piece, calculate the apparent hoop tensile strength at failure σ_{gi} (in kN/m) from the following equation:

$$\sigma_{gi} = \frac{F}{2 W \sin^2 \theta}$$

where

F = failure load, kN;

W = width of test piece, m; and

θ = plane angle between hoop oriented reinforcement and longitudinal axis of the pipe (helix angle).

(CED 50)

Reprography Unit, BIS, New Delhi, India