

AMENDMENT NO. 4 JUNE 2011
TO
IS 12709 : 1994 GLASS FIBRE REINFORCED PLASTICS (GRP) PIPES, JOINTS
AND FITTINGS FOR USE FOR POTABLE WATER SUPPLY —
SPECIFICATION

(First Revision)

(Page 2, Table 1) — Insert the following at appropriate places in ascending order in the table:

Nominal Diameter, DN	Inside Diameter Range, ID		Tolerances on Declared ID
	Min	Max	
1 300	1 295	1 320	±5
1 500	1 495	1 520	±5

[Page 3, Table 2 (see also Amendment No. 1)] — Insert the following at appropriate places in ascending order in the table:

Nominal Diameter, DN	Outside Diameter, OD	Tolerance
1 300	1 330	±5
1 500	1 534	±5

(Page 6, Table 5) — Insert the following at appropriate places in ascending order in the table:

Nominal Diameter	Beam Load	Minimum Longitudinal Tensile Strength in kN/m of Circumference, for Pressure Class				
		PN 3	PN 6	PN 9	PN 12	PN 15
DN	P					
1 300	—	152	226	345	393	468
1 500	—	175	265	397	454	540

(Page 6, Table 6) — Insert the following at appropriate places in ascending order in the table:

Nominal Diameter	Minimum Hoop Tensile Strength of Pipe Wall in kN/m Width of Circumference for Pressure Class				
	PN 3	PN 6	PN 9	PN 12	PN 15
mm					
1 300	790	1 580	2 369	3 159	3 949
1 500	911	1 823	2 734	3 645	4 556

Amend No. 1 to IS 12709 : 1994

(Page 11, clause E-5.3) — Substitute the following for the existing:

‘Load the test piece by separating the mounts at a rate not exceeding 2.5 mm/min and record the maximum force resisted by the test piece.’

(CED 50)

Reprography Unit, BIS, New Delhi, In