

AMENDMENT NO. 1 SEPTEMBER 1986
TO
IS : 2713 (Parts 1 TO 3) - 1980 SPECIFICATION FOR
TUBULAR STEEL POLES FOR
OVERHEAD POWER LINES
PART 1 GENERAL REQUIREMENTS
(Second Revision)

(Page 4, clause 5) — Substitute the following for the existing clause:

“5. MANUFACTURE

5.1 Tubes for manufacturing poles shall conform to Grade YSt 240 or YSt 310 of IS : 1161-1979 ‘Specification for steel tubes for structural purposes (third revision)’, as appropriate. Manual metal arc welding process may also be used to make tubes provided tubes so manufactured shall meet all the requirements of IS : 1161-1979. Cold bend test need not be carried out for tubes manufactured by manual metal arc welding.

5.1.1 For chemical test each coil of sheet/strip used for manufacturing tubes shall be tested for phosphorus and sulphur.

5.1.2 For mechanical tests tubes shall be sampled in accordance with IS : 4711-1974 ‘Methods of sampling of steel pipes, tubes and fittings (first revision)’ depending on the number of tubes in the lot to be inspected.”

(Page 5, clause 8.4) — Substitute the following for existing clause:

‘8.4 The mean weight for bulk supplies shall be within 92.5 percent of its calculated value. The weight of any single pole shall not fall below the nominal weights as given in Part 2 and Part 3 of the standard by more than 10 percent.’

(Page 5, clause 10.1) — Delete ‘(a) Tensile test ... and phosphorus’ and renumber (b), (c) and (d) as (a), (b) and (c).

(Page 5, clause 10.1.1) — Delete.

(Page 5, clause 10.1.2) — Renumber it as 10.1.1.

(Page 6 clauses 10.1.3, 10.1.4 and 10.1.5) — Renumber these as 10.1.2, 10.1.3 and 10.1.4 respectively.

(Page 6, clause 10.2) — Substitute the following for the existing formula:

$$\frac{1}{2L_s} \left[W_1 \left\{ H^2 - \left(l_3 - l_1 - J_1 \right)^2 \right\} + W_2 \left\{ \left(l_3 - l_1 \right)^2 - \left(l_3 - l_1 - J_2 \right)^2 \right\} + W_3 \left(l_3 - l_1 \right)^2 \right].$$

(Page 6, clause 13.1) — Delete the word ‘throughout’ from the third line.

(Page 8, Tabular matter of Fig. 4, column heading D) — Bracketed wording '(Outside Dia of Bottom Plate)' may be read under 'A'.

(Page 8, clause A-1.1) — Substitute the letter symbol 'P', for 'p' and read as under:

"P - Wind pressure on flat surfaces in N/m², to be calculated in accordance with the provisions of IS : 875-1964 'Code of practice for structural safety of buildings: Loading Standards (revised) (With Amendment No. 1)'."

[Page 9, clause A-3.1, (line 7)] — Delete 'h' from the formula

$$N = \frac{p_{nsdh}}{100}$$

[Page 9, clause A-3.2 (lines 4, 7 and 9)] — Substitute 'p' for 'P' in the formulae.

(Page 9, foot-note) — Substitute the following for the existing value:

'1 Newton (N) = 0.102 kgf.
1 kgf = 9.81 N.'

(Page 9, clause A-4.1.1, line 10) — Substitute '2 180' for '2 220'.

(Page 9, clause A-4.1.1, line 11) — Substitute '7.2' for '7.3'.

(Page 9, clause A-4.1.1, line 29) — Substitute '540 TP 28' for '540 TP 38'.

PART 2 SPECIAL REQUIREMENTS FOR POLES MADE FROM STEEL OF TENSILE STRENGTH 410 MPa

(Second Revision)

(Pages 11 to 13, Table 1, col 9) — Substitute 'Nominal Weight of Pole' for 'Approx Weight of Pole'.

(Pages 14 to 16, Table 2, col 12) — Substitute 'Nominal Weight of Pole' for 'Approx Weight of Pole'.

(Page 22, Table 4, col 12, first three items) — Substitute '732.6', '784.5' and '864.7' for '7 732.6', '7 754.5' and '8 864.7' respectively.

PART 3 SPECIAL REQUIREMENTS FOR POLES MADE FROM STEEL OF TENSILE STRENGTH 540 MPa

(Second Revision)

(Pages 25 to 27, Table 1, col 9) — Substitute 'Nominal Weight of Pole' for 'Approx Weight of Pole'.

(Page 26, Table 1, col 11, against designation 540 TP 26) — Substitute '2 180' for '2 810'.

(Pages 28 to 30, Table 2, col 12) — Substitute 'Nominal Weight of Pole' for 'Approx Weight of Pole'.

(SMDC 6)