

AMENDMENT NO. 2 APRIL 1979
TO
IS : 2789-1972 SPECIFICATION FOR
SPECIAL PROOFED PAULINS (TARPAULINS)
(First Revision)

Alteration

(Pages 10 and 11, Appendix B) — Substitute the following for the existing appendix:

‘APPENDIX B
(Clause 4.1)

SAMPLING OF SPECIAL PROOFED PAULINS (TARPAULINS)

B-1. SCALE OF SAMPLING

B-1.1 Lot — In a single consignment all special proofed paulins belonging to the same batch of manufacture shall constitute a lot. If the consignment is declared or known to consist of different batches of manufacture, batches shall be marked separately and the group of proofed special proofed paulins in each batch shall constitute a separate lot.

B-1.2 For ascertaining conformity of material in the lot to the requirements of the specification, samples shall be tested for each lot separately.

B-1.3 The number of pieces of paulins to be selected for this purpose shall depend on the size of the lot and shall be according to col 1 and 2 of Table 1.

TABLE 1 SCALE OF SAMPLING			
No. of Pieces of PAULINS IN THE LOT	FOR NON-CRITICAL REQUIREMENT		SAMPLE SIZE FOR CRITICAL REQUIREMENTS
	Sample Size	Acceptance Number	
(1)	(2)	(3)	(4)
Up to 50	3	0	1
51 to 100	5	0	2
101 to 300	8	0	3
301 to 500	13	1	4
501 and above	20	2	5

B-1.3.1 These paulins shall be selected at random and in order to ensure the randomness of selection, a random number table shall be used. For guidance and use of random number tables, IS : 4905-1968* may be referred. In the absence of a random number table following procedure may be adopted:

Starting from any paulin in the lot, count them in one order as 1, 2, 3, ... , up to r and so on, where r is the integral part of N/n (N and n being the number of paulins in the lot and sample respectively). Every r th paulin so counted shall be withdrawn to constitute the sample.

B-2. NUMBER OF TESTS AND CRITERIA FOR CONFORMITY

B-2.1 The number of paulins, selected according to col 1 and 2 of Table 1 shall be examined for non-critical (visual, dimensional and tactile) requirements. A paulin failing in one or more of these requirements, shall be considered as defective. The lot shall be considered to have satisfied these requirements if the number of defectives found in the sample is less than or equal to the corresponding acceptance number given in col 3 of Table 1.

B-2.2 The number of paulins as given in col 4 of Table 1 shall be tested for critical requirements (other than non-critical). These paulins may be selected from those, already tested and found satisfactory according to B-2.1. A paulin failing in any of these requirements shall be considered as defective. The lot shall be considered to have met these requirements if none of the paulins in the sample is found defective.

B-2.3 The lot shall be declared as conforming to the requirements of the specification if B-2.1 and B-2.2 are satisfied.'

*Method of random sampling.