

AMENDMENT NO. 2 NOVEMBER 1995
TO
IS 2849 : 1983 SPECIFICATION FOR NON-LOAD
BEARING GYPSUM PARTITION BLOCKS (SOLID AND
HOLLOW TYPES)

(*First Revision*)

(*Page 3, clause 0.2*) — Add the following clause after 0.2:

'0.3 Apart from low grade natural gypsum, million tonnes of bye-product phosphogypsum is available from the fertilizer industries. The calcined plaster produced from the phosphogypsum can be used on the production of gypsum partition blocks, panels and boards.'

(*Page 3, clause 0.3*) — Renumber clause '0.3' as '0.4'.

(*Page 3, clause 0.4*) — Renumber clause '0.4' as '0.5' and add the following at the end of this clause:

'Certain additional sizes of gypsum partition blocks have been included in Table 1.'

(*Page 3, clause 0.5*) — Renumber clause '0.5' as '0.6'.

(*Page 4, Table 1*) — Substitute the following for the existing Table 1:

TABLE 1 SIZES OF GYPSUM PARTITION BLOCKS (SOLID AND HOLLOW)				
All dimensions in millimetres.				
LENGTH	HEIGHT	BREADTH	HOLLOW BLOCKS SIDE AND EDGE THICKNESS, <i>M_m</i>	
			Circular Holes	Elliptical or Rectangular Holes
<i>L</i> (1)	<i>H</i> (2)	<i>B</i> (3)	<i>t</i> (4)	<i>t</i> (5)
700 Max in multiples of 100	700 Max in multiples of 100	60	—	—
		75	15	20
		80	—	—
		100	20	20
		125	25	30
		150	15	20

NOTE — Dimensions other than length, height and breadth are for guidance only.

(CED 21)

Reprography Unit, BIS, New Delhi, India