

**AMENDMENT NO. 1 MARCH 2002
TO
IS 2850 : 1983 SPECIFICATION FOR ZINC OXIDE FOR
COSMETIC INDUSTRY**

(Second Revision)

[Page 4, Table 1, Sl No. (iii)] — Substitute the following for the existing:

Sl No.	Characteristics	Requirement	Method of Test (Ref to Cl No. of Appendix A)
iii)	Heavy metals (as Pb)	To pass the test	A-4

(Page 7, clauses A-4 to A-4.3.1) — Substitute the following for the existing:

‘A-4 TEST FOR HEAVY METALS

A-4.1 Reagents

A-4.1.1 Acetic Acid – 1 N.

A-4.1.2 Potassium Chromate Solution (5 percent, m/v).

A-4.2 Procedure – Dissolve 2 g of the material in a mixture of 20 ml water and 5 ml of glacial acetic acid. Add 0.25 ml of potassium chromate solution. The sample shall be taken to have passed the test if solution on addition of potassium chromate solution remains clear.’

(PCD 19)