

**AMENDMENT NO. 2 MAY 2007
TO
IS 2879 : 1998 MILD STEEL FOR METAL ARC
WELDING ELECTRODES —
SPECIFICATION**

(Third Revision)

(Page 2, clause 9.3) — Delete.

(Page 2, clause 10) — Substitute the following for the existing:

'Samples for chemical analysis shall be taken at the rate of one sample for every 25 tonnes or part thereof. For heat size above 100 tonnes, four samples shall be taken and the lot size shall increase proportionally. The shavings or turnings for the purpose of chemical analysis shall be taken across the face of the whole section of the billets, blooms, cast billet ingots or wire rods.

NOTE - A lot shall comprise a part of the material from the same cast.'

(MTD 4)