

**AMENDMENT NO. 3 DECEMBER 2000
TO
IS 2925 : 1984 SPECIFICATION FOR INDUSTRIAL
SAFETY HELMETS**

(Second Revision)

(Page 3, clause 0.4) — Delete clause 0.4.

(Page 5, clause 4.1) — Substitute the following for the existing:

‘Helmets shall be in sizes 520, 530, 540, 550, 560, 570, 580, 590 and 600 mm. These sizes may be generated out of one or more shells or one of more head bands. The size adjustment range shall be clearly marked on the helmet.’

(Page 9, clause 10.1(b)] — Substitute ‘Range/Size’ for ‘Size’.

(Page 10, Appendix A) — Delete.

(Page 13, Appendix G) — Substitute following Appendix G for the existing:

**APPENDIX G
(Clause 8.3)**

METHOD OF TESTING FLAMMABILITY RESISTANCE

G-1 SAMPLE

G-1.1 The samples for testing shall be selected as given in 9.1.

G-2 BURNER

G-2.1 Burner shall be operated with the valve so as to get a flame height of 150 mm. Satisfactory operation of burner shall be checked by inserting in the flame, the bare copper wire of 0.71 mm diameter having a free length of not less than 100 mm in position normally occupied by low edge of the test piece, that is, 50 mm above the burner and reaching farther edge of the flame. The wire should not take more than 6 seconds to melt.

Amend No. 3 to IS 2925 : 1984

G-3 PROCEDURE

G-3.1 With the helmet upside down, and the burner angled at 45° to the vertical. The end of the flame shall be applied to the outside of the shell at any suitable point between 50 and 100 mm from the crown for a period of 10 seconds. The plane tangential to the test point shall be horizontal.

G-3.2 The shell shall be examined for flammability 5 seconds after removal of the flame.

(CED 22)