

**AMENDMENT NO. 2 MAY 2003
TO
IS 13229 : 1991 ZINC FOR GALVANIZING —
SPECIFICATION**

[Page 1, Table 1 (see also Amendment No. 1)] — Substitute the following table for the existing:

**Table 1 Chemical Composition of Zinc for Galvanizing
(Clause 6.1)**

Sl No.	Constituent	Grade Zn 98.50 %
(1)	(2)	(3)
i)	Zinc, <i>Min</i>	98.50
ii)	Lead, <i>Max</i>	1.25
iii)	Cadmium, <i>Max</i>	0.02
iv)	Iron, <i>Max</i>	0.02
v)	Tin, <i>Max</i>	0.02
vi)	Copper, <i>Max</i>	0.02

NOTE — Other impurities do not preclude the possible presence of other unnamed elements. However, analysis shall regularly be made only for the impurities listed in the table. The zinc shall be determined by difference between the sum of total elements analyzed and 100 percent. By agreement between the manufacturer and the purchaser, analysis may be required and limits established for elements not specified.

(MTD 9)