

**AMENDMENT NO. 3 MARCH 2011
TO
IS 13229 : 1991 ZINC FOR GALVANIZING —
SPECIFICATION**

[Page 1, clause 3 (see also Amendment No. 1)] — Substitute the following for the existing:

‘This standard covers Prime Western (PW) grade of zinc for galvanizing with 98.65 %, *Min* of Zinc.’

(Page 1, clause 4.2, third line) — Insert ‘block’ after ‘form of’.

[Page 1, Table 1 (see also Amendments No. 1 and 2)] — Substitute the following for the existing:

Sl No.	Constituent	PW Grade Zn 98.65 %
(i)	Zinc, <i>Min</i>	98.65, <i>Min</i>
(ii)	Lead, <i>Max</i>	1.23
(iii)	Cadmium, <i>Max</i>	0.020
(iv)	Iron, <i>Max</i>	0.020
(v)	Copper, <i>Max</i>	0.020

(Page 1, clause 8.2, second line) — Insert ‘block’ after ‘that is,’.

(MTD 9)