

AMENDMENT NO. 1 DECEMBER 2000
TO
IS 13435 (PART 3) : 1992 ACRYLIC BASED
POLYMER WATERPROOFING MATERIALS —
METHODS OF TEST

PART 3 DETERMINATION OF CAPILLARY WATER TAKE-UP

[*Page 1, clause 3(a)*] — Substitute the following for the existing:

‘a) Specimen of size 240 mm × 240 mm × 45 mm to be cut from aerated concrete block of density 451 to 550 kg/m³, grade 1, having size 600 mm × 250 mm × 200 mm conforming to IS 2185 (Part 3).’

(CED 41)

Reprography Unit, BIS, New Delhi, India