

AMENDMENT NO. 1 MARCH 2018
TO
IS 13528 : 2013 PRETANNING SYNTANS —
SPECIFICATION

(First Revision)

(Page 1, Table 1) — Substitute the following for the existing table:

Table 1 Requirements for Pretanning Syntans
(Clause 4.2)

Sl No.	Characteristic	Requirement	Method of Test, Ref to
(1)	(2)	(3)	(4)
i)	Total solid residue, percent by mass, <i>Min</i> :		
	a) Powder	95.0	8 of IS 13271
	b) Liquid	30.0	
ii)	Moisture, percent by mass, <i>Max</i> :		
	a) Powder	5.0	7 of IS 13271
	b) Liquid	70.0	
iii)	Iron (as Fe ₂ O ₃), percent by mass, <i>Max</i>	0.03	15 of IS 13271
iv)	pH of 10 percent solution	3.0 – 3.5	A-1
v)	PCP content, mg/kg, <i>Max</i>	5.0	17 of IS 13271
vi)	Total free formaldehyde, ppm, <i>Max</i>	50.0	CHD 17 (10756)F ¹⁾

NOTE — The following corrections shall be incorporated while calculating the total solid content for liquid syntan:

$$\text{Total solid, percent by mass} = \frac{M_2}{M_1} \times \frac{1000}{50} \times 100$$

where

M_2 = corrected mass of the material left after drawing, in g;
= $(W - B) + C$.

M_1 = mass of the material taken for the test, in g;

W = mass of the material left after drying, in g;

B = weight of sodium, in g;
= $V \times N \times 0.023$

V = volume of (N) sodium hydroxide solution added; and

C = weight of hydrogen, in g;
= $V \times N \times 0.001$.

¹⁾ Document under printing.