

AMENDMENT NO. 2 JUNE 2021

TO

IS 13592 : 2013 UNPLASTICIZED POLYVINYL CHLORIDE (PVC-U) PIPES FOR SOIL AND WASTE DISCHARGE SYSTEM FOR INSIDE AND OUTSIDE BUILDINGS INCLUDING VENTILATION AND RAIN WATER SYSTEM — SPECIFICATION

(*First Revision*)

[Page 1, clause 2] — Substitute the following for the existing:

‘The following standards contain provisions which, through reference in this text, constitute provision of this standard. At the time of publication the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this standard are encouraged to investigate, the possibility of applying the most recent editions of the standards.

<i>IS No.</i>	<i>Title</i>
4669 : 1968	Method of test for polyvinyl chloride resins
4905 : 2015/ ISO 24153 : 2009	Random sampling and randomization procedures (<i>first revision</i>)
4985 : 2021	Unplasticized PVC pipes for water supplies — Specification (<i>fourth revision</i>)
12235	Thermoplastics pipes and fittings — Methods of test (<i>first revision</i>)
(Part 1) : 2004	Measurement of dimensions
(Part 2) : 2004	Determination of Vicat softening temperature
(Part 4) : 2004	Determining the detrimental effect on the composition of water

Price Group 1

Amendment No. 2 to IS 13592 : 2013

<i>IS No.</i>	<i>Title</i>
(Part 5/Sec 1) : 2004	Longitudinal reversion, Section 1 Determination methods
(Part 5/Sec 2) : 2004	Longitudinal reversion, Section 2 Determination parameters
(Part 6) : 2004	Stress relief test
(Part 7) : 2004	Resistance to sulphuric acid
(Part 9) : 2004	Resistance to external blows (impact resistance) at 0°C (round-the-clock method)
(Part 10) : 2004	Determination of organotin as tin aqueous solution
(Part 11) : 2004	Resistance to dichloromethane at specified temperature
(Part 13) : 2004	Determination of tensile strength and elongation
14182 : 1994	Solvent cement for use with unplasticized polyvinyl chloride plastic pipe and fittings — Specification'

(Page 3, clause 8, Title) — Substitute '**PHYSICAL AND CHEMICAL CHARACTERISTICS**' for '**PHYSICAL TEST REQUIREMENTS**'.

(Page 3, clause 8.2) — Substitute 'IS 12235 (Part 5/sec 1) and IS 12235 (Part 5/ Sec 2)' for 'IS 12235 (Part 5)'.

(Page 3, clause 8.5) — Insert the following at the end:

'8.6 Effect on Water

The pipes shall not have any detrimental effect on the composition of water flowing through them. When tested by the method described in IS 12235 (Part 4) and IS 12235 (Part 10), the quantities of lead, dialkyl tin C4 and higher homologues (measured as tin), and any other toxic substances extracted from the internal walls of the pipes shall not exceed the concentrations as specified in **10.3** of IS 4985 and meet the other requirements given in **10.3.1** of IS 4985.

NOTE — Implementation of the phase out programme for use of lead stabilizers in PVC pipe and fitting manufacturing of the Government of India shall be borne in mind.'

(Page 5, clause 10.2) — Substitute the following for the existing:

‘10.2 Tensile Strength

When determined in accordance with the method described in IS 12235 (Part 13), the tensile strength at maximum load shall not be less than 45 MPa.’

(Page 5, Table 5) — Insert the following new row at the end:

Sl No.	Test	Clause	Acceptance Test	Type Test
(1)	(2)	(3)	(4)	(5)
xiv)	Effect on water	8.6		√

(Page 5, clause 13.2) — Substitute ‘produced’ for ‘produces’.

(Page 5, clause 14.1.1) — Substitute the following for the existing:

‘14.1.1 The information according to 14.1 shall be marked in colour as indicated below for different classes of pipes:

<i>Class of Pipe</i>	<i>Colour</i>
Type A	Blue
Type B	White

14.1.2 The batch number shall include the details of production in the following manner:

Year	Month	Day	Machine No.	Shift
XXXX	XX	XX	XXX	X

14.2.2 BIS Certification Marking

The pipes conforming to the requirements of this standard may be certified as per the conformity assessment schemes under the provisions of the *Bureau of Indian Standards Act, 2016* and the Rules and Regulations framed thereunder, and the pipes may be marked with the Standard Mark.’

(CED 50)