

**AMENDMENT NO. 1 OCTOBER 2008
TO
IS 13645 : 1993 GUNITING THE UPSTREAM FACE
OF MASONRY DAMS — GUIDELINES**

(Page 1, clause 3.1) — Substitute the following for the existing:

‘3.1 Guniting — Guniting is the mortar conveyed on to a surface by means of air pressure applied through a continuously feeding pressure vessel termed as ‘gun’. In this process, the nominal maximum size of aggregate is not more than 4.75 mm.’

[Page 1, clause 4.1(a)] — Substitute ‘IS 269 : 1989’ for ‘IS 269 : 1982’.

(Page 1, clause 4.1) — Insert the following sentence at the end:

‘Flyash conforming to Grade 1 of IS 3812 : 1981 or Calcined clay pozzolana conforming to IS 1344 : 1981 may be used as part replacement of Ordinary Portland cement.’

(Page 1, clause 4.3) — Substitute ‘IS 456 : 2000’ for ‘IS 456 : 1978’.

(Page 1, clause 4.4) — Substitute ‘IS 9103 : 1999’ for ‘IS 9103 : 1979’.

(Page 1, clause 4.5) — Substitute the following for the existing:

‘4.5 Wiremesh — Welded wire fabric used shall conform to IS 1566 : 1982. For Guniting more than 25 mm thick, use of wiremesh may be preferred.’

(Page 1, clauses 4.1, 4.2, 4.3, and 4.4) — Substitute the word ‘shall’ for ‘should’ wherever appears.

(Page 2, clause 6.1) — Substitute ‘IS 456 : 2000’ for ‘IS 456 : 1978’.

(Page 2, clause 7.1, line 2) — Substitute ‘cementitious material’ for ‘cement’.

(Page 2, clause 7.2.1, line 3) — Substitute ‘the sand-cementitious material mixture’ for ‘the sand-cement mixture’.

Amend No. 1 to IS 13645 : 1993

(Page 3, clauses 13 and 14) — Substitute 'shall' for 'should' wherever appears.

(Page 4, Annex A) — Substitute 'IS 456 : 2000' for 'IS 456 : 1978' and 'IS 9103 : 1999' with 'IS 9103 : 1979'.

(WRD 9)

Reprography Unit, BIS, New Delhi, India