

AMENDMENT NO. 2 FEBRUARY 1998
TO
IS 2519 : 1983 SPECIFICATION FOR CALCIUM
STEARATE FOR COSMETIC INDUSTRY
(Second Revision)

(Page 6, clause A-2) — Substitute the following for the existing:

A-2 DETERMINATION OF CALCIUM

A-2.1 Reagents

A-2.1.1 Sulphuric Acid — 0.1 N.

A-2.1.2 Disodium Ethylenediamine Tetra Acetate — 0.05 M.

A-2.1.3 Sodium Hydroxide Solution — 20% W/V.

A-2.1.4 Calcon Mixture — Mix one part of calcon with 99 parts of sodium chloride.

A-2.2 Procedure — Weigh accurately about 1 g of the material and boil with 50 ml of 0.1 N Sulphuric acid until the fatty acid layer which separates is clear, adding more water as necessary to maintain the original volume, cool and filter. Wash thoroughly with water until the last wash is not acid to litmus paper. Combine filtrate and washings and dilute to approximately 50 ml with water and titrate with 0.05 M disodium EDTA to within a few ml of expected end point. Add 8 ml of Sodium hydroxide solution and 0.1 g of calcon mixture and continue the titration until the colour of the solution changes from pink to a full blue colour.

A-2.3 Calculation

$$\text{Calcium as CaO,} \\ \text{percent by mass} = \frac{5.608 \times V \times M}{W}$$

where

V = volume of disodium EDTA solution,

M = molarity of disodium EDTA solution, and

W = weight of the sample.

(PCD 19)