

AMENDMENT NO. 1 DECEMBER 1995
TO
IS 2520 : 1984 SPECIFICATION FOR ZINC
STEARATE FOR COSMETIC INDUSTRY

(*Second Revision*)

[Page 4, Table 1, Sl No. (i), col 3] — Substitute '12.5 to 14.5' for '13.0 to 15.5'.

(Page 6, clause A-2, *Determination of Zinc*) — Substitute the following for the existing:

'A-2.1 Reagents

A-2.1.1 Sulphuric Acid — 0.1 N.

A-2.1.2 Strong Ammonia — Ammonium Chloride solution — Dissolve 67.5 g of Ammonium Chloride in 740 ml of Ammonia solution (25% w/w) and add sufficient water to produce 1 000 ml.

A-2.1.3 Erichrome Black T Solution — Dissolve 0.20 g of Erichrome Black T and 2 g of Hydroxylamine hydrochloride in sufficient methyl alcohol to produce 50 ml. This solution must be freshly prepared.

A-2.1.4 Standard Disodium Ethylenediamine Tetra Acetate Solution — 0.05 M.

A-2.2 Procedure — Weight accurately about 1 g of material and boil with 50 ml of 0.1N Sulphuric acid until the fatty acid layer which separates is clear, adding more water as necessary to maintain the original volume; cool and filter. Wash thoroughly with water until the last washing is not acid to litmus paper. Add to the combined filtrate and washings, 15 ml of strong Ammonia — Ammonium Chloride solution and 0.2 ml of Erichrome Black T Solution. Heat the solution to about 40°C and titrate with 0.05M Disodium Ethylenediamine tetra acetate until the solution is deep blue in colour.

A-2.3 Calculation

$$\text{Zinc as ZnO, percent by mass} = \frac{8.138 \times V \times M}{m}$$

where

V = volume in ml of Disodium Ethylenediamine tetra acetate solution,

M = molarity of Disodium Ethylenediamine tetra acetate solution, and

m = weight of the material in g.