

AMENDMENT NO. 2 DECEMBER 1995 TO IS 2547 (Part 1) : 1976 SPECIFICATION FOR GYPSUM BUILDING PLASTER

PART 1 EXCLUDING PREMIXED LIGHTWEIGHT PLASTERS

(First Revision)

(Page 5, clause 4.1, Table 1) — Insert 'β-hemihydrate' in col 3 under Plaster of Paris.

(Page 5, Table 1) — Substitute '1982' for the existing year '1973' in col 7.

(Page 5, clause 5.1, line 3) — Insert 'sodium sulphate' after 'potassium sulphate'.

(Page 5, clause 5.1, line 4) — Insert 'such as Alkyl-Aryl sulphonate' after 'working characteristics' and 'such as nitrates and nitrites of alkali metals' after 'anti-corrosion'.

(Page 6, clause 5.2, line 2) — Substitute '1978' for the existing year '1964'.

(Page 6, Table 2) — Substitute the following for the existing table:

TABLE 2 PHYSICAL REQUIREMENTS

SL No.	PARTICULARS	REQUIREMENT			
		Plaster of Paris		Anhydrous Gypsum Plaster	Keene's Plaster
		Type A (short time setting)	Type B (long time setting)		
(1)	(2)	(3)	(4)	(5)	(6)
i)	Setting time minutes:	—	—	—	—
	a) Plaster sand mixture	45-120	120-900	—	—
	b) Neat plaster	20-40	60-180	20-360	20-360

Amend No. 2 to IS 2547 (Part 1) : 1976

TABLE 2 (Concluded)

SL No.	PARTICULARS	REQUIREMENT			
		Plaster of Paris		Anhydrous Gypsum Plaster	Keene's Plaster
		Type A (short time setting)	Type B (long time setting)		
(1)	(2)	(3)	(4)	(5)	(6)
ii)	Transverse strength, kg/cm ² , <i>Min</i>	5	4*	—	—
iii)	Soundness	Set plaster pats shall not show any sign of disintegration, popping or pitting	Set plaster pats shall not show any sign of disintegration, popping or pitting	Set plaster pats shall not show any sign of disintegration, popping or pitting	Set plaster pats shall not show any sign of disintegration, popping or pitting
iv)	Mechanical resistance of set neat plaster	—	†Diameter of the indentation shall not be less than 3 mm and not more than 4.5 mm	Diameter of the indentation shall not be more than 4 mm	Diameter of the indentation shall not be more than 3.5 mm
v)	Residue on 90 µm sieve percentage, <i>Max</i>	5.0	5.0* (1.0)†	2.0	2.0
vi)	Expansion on setting percentage, <i>Max</i>	—	0.20 at 24 h‡	—	0.5 at 96 h

*Applicable to undercoat plasters only.

†Applicable to final coat plasters.

‡Applicable to board finish plasters only.

(Page 7, clause 6.3.1, line 4) — Substitute '90 µm' for '1.18 - mm IS' before 'sieve'.

(Page 9, clause A-1-1, line 2) — Substitute 'IS 460 (Part 1) : 1985' for 'IS : 460 - 1962'.

(Page 9, foot-note with '*' mark) — Substitute '*Specification for test sieves : Part 1 Wire cloth test sieves (third revision)' for the existing.

(CED 21)