

AMENDMENT NO. 1 AUGUST 1992
TO
IS 4588 : 1986 SPECIFICATION FOR RUBBER, RAW, NATURAL
(Third Revision)

(Page 4, clause 5.1) — Insert the following new clause after 5.1:

‘5.1.1 An identification strip of polyethylene bearing the colour as indicated in the following colour code shall be wrapped on each bale:

Grade	ISNR 3 CV	ISNR 3L	ISNR 5	ISNR 10	ISNR 20	ISNR 50
Colour Code	Black	Black	Green	Brown	Red	Yellow

(Page 5, Table 1) — Substitute the following for the existing table:

Table 1 Physical and Chemical Requirements for Rubber, Raw, Natural
(Clauses 3.1 and 4.2)

Sl. No.	CHARACTERISTIC	REQUIREMENTS FOR						METHOD OF TEST, REF TO
		ISNR 3 CV	ISNR 3L	ISNR 5	ISNR 10	ISNR 20	ISNR 50	
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)
i)	Dirt content, percent by mass, <i>Max</i>	0.03	0.03	0.05	0.10	0.20	0.50	IS 3660 (Part 1) : 1985 ^a
ii)	Volatile matter, percent by mass, <i>Max</i>	0.80	0.80	0.80	0.80	0.80	0.80	IS 3660 (Part 2) : 1985 ^a
iii)	Ash, percent by mass, <i>Max</i>	0.50	0.50	0.60	0.75	1.00	1.50	IS 3660 (Part 3) : 1988 ^a
iv)	Nitrogen, percent by mass, <i>Max</i>	0.6	0.6	0.6	0.6	0.6	0.6	NR : 11 of IS 3660 (Part 52) : 1968 ^a
v)	Initial plasticity ^a	As agreed to between the purchaser and the supplier	30 (Min)	30 (Min)	30 (Min)	30 (Min)	30 (Min)	IS 3660 (Part 11) : 1989 ^a
vi)	Plasticity retention index (PRI) ^b , <i>Min</i>	60	60	60	50	40	30	IS 3660 (Part 12) : 1989 ^a
vii)	Colour (Lovibond scale), <i>Max</i>	—	6.0	—	—	—	—	NR : 14 of IS 3660 (Part 54) : 1979 ^a
viii)	Mooney viscosity ML ₁₊₄ at 100°C	60±5	—	—	—	—	—	IS 3660 (Part 7) : 1988 ¹⁰
ix)	Accelerated storage hardening, ΔP	8 (Max)	—	—	—	—	—	NR : 15 of IS 3660 (Part 54) : 1979 ^a

- 1 Methods of test for natural rubber: Part 1 Determination of dirt (NR : 1) (*second revision*).
- 2 Methods of test for natural rubber: Part 2 Determination of volatile matter (NR : 2) (*second revision*).
- 3 Methods of test for natural rubber: Part 3 Determination of ash (NR : 3) (*second revision*).
- 4 Methods of test for natural rubber: Part 52 Determination of nitrogen content (*under revision*).
- 5 In parallel plate plastimeter [as described in 4.1 of IS 3660 (Part 11) : 1989], one platen of 10.0 mm diameter shall be used.
- 6 Method of test for natural rubber: Part 11 Determination of plasticity (NR : 12) (*first revision*).
- 7 Temperature recovery of the oven and the inserted tray and dishes to within 1°C of the set temperature in a time not exceeding six minutes [in place of two minutes as described in 4.4(b) of IS 3660 (Part 12) : 1989] after insertion of the tray in the oven.
- 8 Methods of test for natural rubber: Part 12 Determination of plasticity retention index (NR : 13) (*first revision*).
- 9 Methods of test for natural rubber, Part 54 Determination of colour, accelerated storage-hardening test and vulcanization characteristics (MOD test).
- 10 Methods of test for natural rubber: Part 7 Determination of mooney viscosity (NR : 8) (*second revision*).