

AMENDMENT NO. 1 OCTOBER 1985

TO

IS:4606-1983 SPECIFICATION FOR STEEL SHOT FOR
USE IN FOUNDRIES

(First Revision)

(Pages 9 and 10, clauses B-3.1 and B-4.1) -
Substitute the following for the existing clauses:

'B-3.1 From each of the selected containers as in Column 1 and Column 2 of Table 2, with the help of a suitable sampling instrument, draw 1 kg material if the number of sample containers is less than or equal to 8 and 0.5 kg material when the number of sample containers is greater than or equal to 13. This material shall be taken from the top, centre or bottom of each selected containers. Samples taken from all the selected containers shall be mixed to form a composite sample. From this, 4 kg shall be kept apart as size sample for size analysis and rest of the composite sample shall be reduced by successive coning and quartering division method to give a final sample of 300 g. This final sample shall be divided into three equal portions, one for the purchaser, the second for the manufacturer and the third shall be kept as a referee sample.'

B-4.1 The size sample collected as per B-3.1 shall be used for size analysis and the test sample shall be used for chemical analysis, hardness and microstructure characteristics.'

(SMDC 17)