

AMENDMENT NO. 1 AUGUST 1987

TO

**IS:4712-1984 SPECIFICATION FOR FORGED STEEL,
 SOCKET-WELDING FITTINGS**

(First Revision)

(Page 4, clause 4.1) - Substitute the following for the existing clause and renumber 4.1.1 as 4.1.2 and the subsequent clauses as 4.1.3, 4.1.4 and 4.1.5:

"4.1 Chemical Composition - The steel from which forged steel socket welding fitting is made shall conform to the chemical composition given below:

<u>Elements</u>	<u>Composition, Percent</u>	<u>Variation from the Specified Limits, Percent</u>
Carbon	0.35, <u>Max</u>	Up to 0.25 $\pm$ 0.02 from 0.25 $\pm$ 0.03 to 0.35
Manganese	0.60-1.05	-
Phosphorus	0.040, <u>Max</u>	+ 0.005
Sulphur	0.050, <u>Max</u>	+ 0.005
Silicon	0.35, <u>Max</u>	$\pm$ 0.03

NOTE - For each reduction of 0.01 percent below the specified carbon, Max (0.35 percent), an increase of 0.06 percent

manganese above the specified, Max (1.05 percent) will be permitted up to a maximum of 1.35 percent.

4.1.1 The analysis of steel shall be carried out either by the method specified in IS:228 'Methods for chemical analysis of steels' and its relevant parts or any other established instrumental/chemical method. In case of dispute the procedure given in IS:228 and its relevant parts shall be referee method. However, where the method is not given in IS:228 and its relevant parts, the referee method shall be agreed to between the purchaser and the manufacturer."

(SMDC 22)