

AMENDMENT NO. 1 MAY 1989
TO
IS : 4736 - 1986 SPECIFICATION FOR HOT-DIP
ZINC COATINGS ON MILD STEEL TUBES

(First Revision)

(Page 4, Note under clause 5.1) — Substitute the following for the existing note:

'NOTE — Mass of zinc coating shall not be less than 400 g/m² as determined from the average result of two specimens taken from opposite ends of tube selected for testing. The lower of the two values shall not be less than 360 g/m².'

(SMDC 28)

Reprography Unit, BIS, New Delhi, India