

**AMENDMENT NO. 3 MAY 2002
TO
IS 4736 : 1986 SPECIFICATION FOR HOT-DIP ZINC
COATINGS ON MILD STEEL TUBES**

(First Revision)

(*Amendment No 1*) — Withdrawn

(*Page 4, clause 5.1*) — Substitute the following for the existing

'5.1 Mass of Zinc Coating — For tubes with thickness up to 6 mm, the minimum mass of zinc coating, when determined on a 100 mm long test piece (*see 6.2*) in accordance with IS 6745 1972‡ shall be 360 g/m^2

NOTE — Mass of zinc coating shall not be less than 360 g/m^2 when tested on two specimens taken from opposite ends of the tube selected for testing

(*Page 5, clause 5.4*) — Substitute the following for the existing

'5.4 Uniformity of Galvanized Coating — The galvanized coating when determined on a 100 mm long test piece (*see 6.2*) in accordance with IS 2633 1986* shall withstand 5 one minute dips '

(MTD 24)