

AMENDMENT NO. 2 JUNE 2005
TO
IS 4834 : 1968 SPECIFICATION FOR
VENEERED-WOOD BOARDS FOR PACKING CASES

(*Page 3, Foreword, clause 0.2.1, line 6*) — Substitute 'IS 1659 : 2004^{*}' for 'IS 1659 : 1960^{*}'.

(*Page 3, footnote marked '*'*) — Substitute the following for the existing:

^{*}'Black boards — Specification (*fourth revision*)

(*Page 4, clause 2.0, line 2*) — Substitute 'IS 707 : 1976^{*}' for 'IS 707 : 1968^{*}'.

(*Page 4, footnote marked '*'*) — Substitute the following for the existing:

^{*}'Glossary of terms applicable to timber technology and utilization (*second revision*).'

(*Page 4, clause 3*) — Substitute the following for the existing:

'3 GRADE

3.1 Veneered-wood board shall be of MR grade for both storage as well as transit packs.'

(*Page 4, clause 4*) — Substitute the following for the existing:

'4 MATERIALS

4.1 Timber

4.1.1 Any species of timber may be used for face veneer and core. However, a list of species is given in Annex B of IS 303 : 1989[†] for guidance.

4.2 Adhesives

The adhesive used for bonding purpose shall be of MR type conforming to IS 848 : 1974[‡].

(*Page 4, footnotes marked '†' and '‡'*) — Substitute the following for the existing:

^{*}'Specification for plywood for general purposes (*third revision*) .

[‡]'Specification for synthetic resin adhesives for plywood (phenolic and aminoplastic) (*first revision*).'

[*Page 8, Annex C (see also Amendment No. 1)*] — Substitute the following for the existing:

ANNEX C
(*Clause 9.5*)

TEST FOR RESISTANCE TO WATER

C-1 PROCEDURE

C-1.1 The test specimens shall be submerged in a pan of cold water, care being taken that the pieces do not touch the bottom of the pan. The water shall be heated to $60 \pm 2^{\circ}\text{C}$ and maintained at this temperature for 3 h. After this, the test specimens shall be removed from the hot water and plunged immediately into cold water. While still water-soaked, the test specimens shall be tested by forcibly separating the outer layers, using a prising knife.'

[*Page 9, clause D-1.4, line 2 (see also Amendment No. 1)*] — Substitute 'three weeks' for 'two weeks'.